

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



# Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China







## SPECIFICATION CONTROL DRAWING

100 OHM, AWG 24, 19 STRANDS OF AWG 36.

0024S1664 10-23-12 Date

**CHEMINAX** 

TWINAXIAL CABLE, OUTER SPACE USE

Revision

100 ± 10 ohms, Method C at 1 MHz

26.5 ohms/1000 ft. (nominal)

.750 lb., 2.5 kV dielectric test

50% (minimum)

5000 lbf/in2 (minimum)

300 ± 3°C for 1 hour, .875 inch mandrel,

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

## CONSTRUCTION DETAILS


ELECTRICAL CHARACTERISTICS

ADDITIONAL REQUIREMENTS

**COMPONENT WIRE PRIOR TO CABLING (Test Procedures per SAE AS22759)** 

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED

**MUTUAL CAPACITANCE** 16.0 pF/ft. (nominal)



.167

.185

#### CONDUCTORS

AWG 24, 19 Strands of AWG 36, Silver-Coated High-Strength Copper Alloy

#### **DIELECTRICS**

SHIELD

AWG 38.

**JACKET** 

Silver-Coated Copper

Radiation-Crosslinked.

Modified ETFE

Radiation-Crosslinked. Modified ETFE (Dual Extruded) Colors - Light Blue/White

## INSULATION (DIELECTRIC)

CONDUCTOR RESISTANCE

CROSSLINKING PROOF TEST

(Total Insulation) ELONGATION TENSILE STRENGTH

CHARACTERISTIC IMPEDANCE

**INSULATION FLAWS** SPARK TEST 3.0 kV (rms)

**IMPULSE TEST** 8.0 kV (peak) INSULATION RESISTANCE

5000 megohms for 1000 ft. (minimum) LOW TEMPERATURE-COLD BEND -65 ± 3°C for 4 hours, .500 inch mandrel, 1.00 lb., 2.5 kV dielectric test

200 ± 3°C for 1 hour,

**SHRINKAGE** 

.125 inch (maximum) in 12 inches

## **FINISHED CABLE**

### (Test Procedures per NEMA WC 27500, unless otherwise specified)

**BLOCKING** 200°C for 6 hours

CROSSLINKED VERIFICATION 300 ± 5°C for 6 hours, 6.00 inch mandrel **FLAMMABILITY** 3 seconds (maximum); 3 inches (maximum); no flaming of facial tissue

(Method B of Spec 1200)

**JACKET** 

**ELONGATION** 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

JACKET FLAWS

SPARK TEST 1.0 kV (rms) IMPULSE TEST 6.0 kV (peak) .009 inch (nominal) **JACKET THICKNESS** LOW TEMPERATURE-COLD BEND -55 ± 5°C for 4 hours, 6.00 inch mandrel

SHIELD COVERAGE

**VOLTAGE WITHSTAND** (DIELECTRIC)

1500 volts (rms)

20.1 lbs/1000 ft. (nominal) WEIGHT

Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 0024S1664-9) unless otherwise specified.

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

## **OUTER SPACE REQUIREMENTS**

90% (minimum)

RADIATION RESISTANCE 500 megarads/5.50 inch mandrel 1.0 kV dielectric test

**VACUUM STABILITY** 

TOTAL MASS LOSS (TML) 1.00% (maximum) **VOLATILE CONDENSABLE** 0.10% (maximum) MATERIAL (VCM)

WEIGHT LOSS: 0.45% (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Page 1 of 1

Cheminax, Raychem, TE Connectivity, TE connectivity (logo) and TE (logo) are trademarks

