imall

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China







SPECIFICATION


(Reference sheet)

- Supplier : Samsung electro-mechanics
- Product : Multi-layer Ceramic Capacitor
- Samsung P/N :
- CL03C8R2BA3GNNC
- Description :
- CAP, 8.2pF, 25V, ±0.1pF, C0G, 0201

A. Samsung Part Number

			<u>CL</u>	<u>03</u>	<u>C</u>	<u>8R2</u>	B	<u>A</u>	<u>3</u>	<u>G</u>	N	N	<u>C</u>				
			1	2	3	4	5	6	1	8	9	10	1				
1	Series	Samsung	g Multi-la	yer C	eram	nic Cap	acito	or									
2	Size	0201	(inch co	ode)		L:	0.60	± 0.0	3	mm		W:	0.30	± 0.03	mm		
3	Dielectric	C0G	6				8	Inner	elec	trode	•		Cu				
4	Capacitance	8.2	рF					Term	inati	on			Cu				
5	Capacitance	±0.1	рF					Plati	ng				Sn 10	0%	(Pb F	ree)	
	tolerance						9	Prod	uct				Norm	al			
6	Rated Voltage	25	V				10	Spec	ial				Reser	ved for	future	use	
\bigcirc	Thickness	0.30	± 0.03	mm			1	Pack	aging	g			Cardb	oard Ty	/pe, 7"	reel	

B. Structure and dimension



Samsung P/N	Dimension(mm)								
(Lead Free)	L	W	Т	BW					
CL03C8R2BA3GNNC	0.60±0.03	0.30±0.03	0.30±0.03	0.15±0.05					

C. Samsung Reliability Test and Judgement condition

	Performance	Test condition				
Capacitance	Within specified tolerance	1₩±10% 0.5~5Vrms				
Q	564 min					
Insulation	10,000Mohm or 500Mohm . <i>μ</i> F	Rated Voltage 60~120 sec.				
Resistance	Whichever is smaller					
Appearance	No abnormal exterior appearance	Microscope (×10)				
Withstanding	No dielectric breakdown or	300% of the rated voltage				
Voltage	mechanical breakdown					
Temperature	COG					
Characteristics	(From -55℃ to 125℃, Capacitance change should be within ±30PPM/℃)					
Adhesive Strength	No peeling shall be occur on the	200g F, for 10±1 sec.				
of Termination	terminal electrode					
Bending Strength	Capacitance change :	Bending to the limit (1mm)				
	within $\pm 5\%$ or ± 0.5 pF whichever is larger	with 1.0mm/sec.				
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder				
	is to be soldered newly	245±5℃, 3±0.3sec.				
		(preheating : 80~120℃ for 10~30sec.)				
Resistance to	Capacitance change :	Solder pot : 270±5℃, 10±1sec.				
Soldering heat	within $\pm 2.5\%$ or ± 0.25 pF whichever is larger					
	Tan δ, IR : initial spec.					
Vibration Test	Capacitance change :	Amplitude : 1.5mm				
	within ±2.5% or ±0.25pF whichever is larger	From 10Hz to 55Hz (return : 1min.)				
	Tan δ, IR : initial spec.	2hours \times 3 direction (x, y, z)				
Moisture	Capacitance change :	With rated voltage				
Resistance	within $\pm 7.5\%$ or ± 0.75 pF whichever is larger	40±2℃, 90~95%RH, 500+12/-0hrs				
	Q: 127.33 min					
	IR : 500Mohm or 25Mohm · <i>μ</i> F					
	Whichever is smaller					
High Temperature	Capacitance change :	With 200% of the rated voltage				
Resistance	within ±3% or ±0.3pF whichever is larger	Max. operating temperature				
	Q : 282 min	1000+48/-0hrs				
	IR : 1,000Mohm or 50Mohm · μF					
	Whichever is smaller					
Temperature	Capacitance change :	1 cycle condition				
Cycling	within $\pm 2.5\%$ or ± 0.25 pF whichever is larger	Min. operating temperature \rightarrow 25 °C				
	Tan δ, IR : initial spec.	→ Max. operating temperature → 25° C				
		5 cycle test				

* The reliability test condition can be replaced by the corresponding accelerated test condition.

D. Recommended Soldering method :

Reflow (Reflow Peak Temperature : 260+0/-5°C, 10sec. Max)

A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.

- Disclaimer & Limitation of Use and Application -

The products listed in this Specification sheet are **NOT** designed and manufactured for any use and applications set forth below.

Please note that any misuse of the products deviating from products specifications or information provided in this Spec sheet may cause serious property damages or personal injury. We will **NOT** be liable for any damages resulting from any misuse of the products, specifically including using the products for high reliability applications as listed below.

If you have any questions regarding this 'Limitation of Use and Application', you should first contact our sales personnel or application engineers.

- Aerospace/Aviation equipment
- 2 Automotive or Transportation equipment (vehicles, trains, ships, etc)
- 3 Medical equipment
- *④ Military equipment*
- *5* Disaster prevention/crime prevention equipment
- *(6)* Any other applications with the same as or similar complexity or reliability to the applications set forth above.