



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



# ECCOSORB® SS Tapes

High Tack Pressure Sensitive Adhesive (PSA) Tapes

## Material Characteristics

- ECCOSORB® SS-tapes are very high tack pressure sensitive adhesive (PSA) tapes specifically designed for use with Emerson & Cuming Microwave Product's absorbers
- There are several PSA's offered:
  - ECCOSORB® SS6M for silicone absorbers
  - ECCOSORB® SS3 for urethane absorbers
  - ECCOSORB® SSV for vinyl materials
  - ECCOSORB® SS9 for ECCOSTOCK® PP
- ECCOSORB® SS-tapes are cleanly cut with steel roll dies or via water-jet cutting

## Applications & Testing

- ECCOSORB® SS-tapes are used throughout many applications where high bond reliability and UV resistance is required
- ECCOSORB® SS-tapes are ideally suited for applications such as commercial microwave devices where the speed and convenience of a peel and stick adhesive is desired
- ECCOSORB® SS6M has been shown effective in applications involving shock and vibration, temperature cycling and high humidity
- Adhesion testing with SS6M was also performed with material attached to a housing at 200 °F for 24 hours, mounted at 90°, and heated to 300 °F for 24 hours. No slouching was seen and bond strength is excellent!
- In general longer residence time yields higher peel values

## Availability

- ECCOSORB® SS-tapes are factory installed, which utilize a proprietary process resulting in a superior adhesive bond. When applied in this manner, bond strength is far superior when compared to those adhesives applied to the material after its manufacture

## Instructions for Use

- Simply peel the release paper off of the adhesive backing and apply
- The use of heat and pressure will help to increase the initial bond of the material to the substrate. Surfaces to be bonded should be cleaned, dry, and free from grease and oil
- ECCOSORB® SS3 and SS6M should not be bonded to any material that may contain migrating plasticizers, rather SSV should be used

## Typical Properties

	SS6M	SS3	SS9	SSV
Adhesive Type	Acrylic	Acrylic	Synthetic Rubber	Acrylic
Adhesive Carrier	0.5 mil Polyester	0.5 mil Polyester	4.0 mil Polyethylene	0.5 mil Polyester
Tape Thickness	4.5 mils	4.5 mils	45.7 mils	3.1 mils
Peel adhesion to steel (lb./inch width)	4.7	4.7	-	4.7
Tensile Strength, lb./in.	10	10	-	10
Elongation	60%	60%	-	60%
Typical Service Temperature, °F (°C)	-40 to 250 (-40 to 121)	-40 to 250 (-40 to 121)	30 to 150 (-1.1 to 66)	-40 to 250 (-40 to 121)
Material Type	Silicone Absorber	Urethane Absorber	ECCOSTOCK® PP	Vinyl

EMERSON & CUMING MICROWAVE PRODUCTS, INC., 28 York Avenue, Randolph, MA 02368 / Telephone (781) 961-9600. Use of Information and Material: Values shown are based on testing of laboratory test specimens and represent data that falls within normal range of the material. These values are not intended for use in establishing maximum, minimum or ranges of values for specification purposes. Any determination of the suitability of the material for any purpose contemplated by the user and the manner of such use is the responsibility of the user. The user should determine that the material meets the needs of the user's product and use. We hope that the information given here will be helpful. It is based on data and knowledge considered to be true and accurate and is offered for the user's consideration, investigation and verification but we do not warrant the results to be obtained. Please read all statements, recommendations or suggestions in conjunction with our conditions of sale INCLUDING THOSE LIMITING WARRANTIES AND REMEDIES, which apply to all goods supplied by us. We assume no responsibility for the use of these statements, recommendations or suggestions nor do we intend them as a recommendation for any use, which would infringe any patent or copyright. Emerson & Cuming Microwave Products Inc.