



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts,Customers Priority,Honest Operation,and Considerate Service",our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





LOCTITE[®] 7387

July 2004

PRODUCT DESCRIPTION

LOCTITE[®] 7387 provides the following product characteristics:

Technology	Activator for Loctite toughened acrylic adhesives
Chemical Type	Substituted dihydropyridine
Solvent	n-Heptane and Isopropanol
Appearance	Transparent yellow to light amber liquid ^{LMS}
Viscosity	Very low
Cure	Not applicable
Application	Cure promotion of toughened acrylic adhesives

LOCTITE[®] 7387 is designed to initiate the cure of Loctite toughened acrylic adhesives.

TYPICAL PROPERTIES

Specific Gravity @ 25 °C	0.80
Viscosity @ 25°C, mPa·s (cP)	1 to 2
Flash Point - See MSDS	

TYPICAL PERFORMANCE

Fixture time and cure speed achieved as a result of using LOCTITE[®] 7387 depend on the adhesive used, the substrate bonded, surface cleanliness and whether one or two surface activation is used.

Fixture Time, ISO 4587, minutes:

Steel (grit blasted) and Loctite [®] Adhesive 330, single side activation	≤4 ^{LMS}
------------------------------------------------------------------------------------	-------------------

(Fixture time is defined as the time to develop a shear strength of 0.1 N/mm²)

HANDLING PRECAUTIONS

Activator must be handled in a manner applicable to highly flammable materials and in compliance with relevant local regulations.

The solvent can affect certain plastics or coatings. It is recommended to check all surfaces for compatibility before use.

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected with a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Under no circumstances should activator and adhesive be mixed directly as liquids. Use only in a well ventilated area.

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

Directions for use

1. Most surfaces may be bonded "as received" but contamination such as loose oxide layers or excessive oil may affect cure speed and bond strength. Cleaning is recommended if maximum strength is required.
2. Brush on the activator to one of the mating surfaces to be bonded. Apply adhesive to other surface.
3. For large gaps (>0.40 mm) or where maximum cure speed is required then treatment of both surfaces is recommended.
4. The activator will not dry and will remain active for up to 6 hours. Bond assembly should be completed within this time.
5. Where adhesive is applied onto an activated surface, assembly should be completed as quickly as possible (within 15 seconds).
6. Secure the assembly and await fixturing before any further handling.

Loctite Material Specification^{LMS}

LMS dated July 08, 2004. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Loctite Quality.

Storage

This activator is classified as **HIGHLY FLAMMABLE** and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidising agents or combustible materials. The product is light sensitive and accordingly, translucent containers should be kept in a dark place when not in use. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
kV/mm x 25.4 = V/mil
mm / 25.4 = inches
N x 0.225 = lb
N/mm x 5.71 = lb/in
N/mm ² x 145 = psi
MPa x 145 = psi
N·m x 8.851 = lb·in
N·mm x 0.142 = oz·in
mPa·s = cP

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

LOCTITE is a trademark of Henkel Corporation

Reference 1