



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



Ratings

Voltage: 300 V
 Temperature: 80 °C
 Flammability: VW-1, FT1

Conductor

Conductor count: 6
 Gauge: 24 AWG, 0.22 mm²
 Material: tinned copper strands
 Stranding: $\phi 0.16 \times 11$
 Resistance at 20 °C: 95 ohm/km maximum

Insulator

Material: SRPVC, 80 °C
 Color: black, white, red, yellow, blue, green
 Outer diameter: $\phi 1.2 \pm 0.10$ mm
 Thickness: 0.23 mm minimum average
 Style: UL 1061

Outer jacket

Material: PVC, 80 °C
 Color: black
 Diameter: $\phi 4.9 \pm 0.30$ mm
 Thickness: 0.76 mm minimum average



Wire marking: E339579 UL AWM STYLE 2464 24AWG 80°C
 300V VW-1 --- cUL AWM I A 80°C 300V FT1 TENSILITY

Tests

Tensile strength: 1.05 kgf/mm²
 After aging at 113 ± 2 °C for 7 days:
 Minimum tensile strength 70 % original
 Minimum elongation 65 % original
 Flexibility: no observed cracking
 Heat shock: 121 ± 1 °C /1 hour, no observed degradation
 Deformation: 121 ± 1 °C /1hour, ≤ 50 %
 Cold bend: -10 ± 2 °C /1 hour, no observed cracking
 Dielectric: 2000 Vac for 1 minute without breakdown

Use:

Internal wiring or external interconnection of electronic equipment



REVISION	DATE	DESCRIPTION	PREPARED:	NOTES	<h1>TENSILITY</h1> <p>20802 Sockeye Place #130 Bend, OR 97701 USA tel 541.323.3228 fax 541.323.4202 800 877.670.7118 www.tensility.com</p>			
A	10/13/2015	Initial release	AG 2016.01.26 07:52:56 -08'00'	RoHS and REACH compliant				
A1	1/26/2016	updated dimensions	LA Digitally signed by LA, DN: cn=LA, o=Tensility, ou=Engineering, email=C6000@Tensility.com, c=US Date: 2016.01.26 16:46:11 -0800'	Function test: no open, no short circuit, no intermittent Meets UL appliance wiring standard 758				
			DIMENSIONS ARE IN MILLIMETERS	DESCRIPTION: Wire, 6C TS, 24 AWG, UL2464, 300V, 80C, 4.9 mm, VW-1, PVC				
			TOLERANCES: X: ± 0.5 mm X.X: ± 0.3 mm X.XX: ± 0.05 mm	<table border="1"> <tr> <td>SIZE</td> <td>PART NUMBER</td> </tr> <tr> <td>A</td> <td>30-00507</td> </tr> </table>		SIZE	PART NUMBER	A
SIZE	PART NUMBER							
A	30-00507							
			SCALE: 1:1		SHEET 1 OF 1			