imall

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



Ratings

Voltage: 300 V Temperature: 80 °C Flammability: VW-1, FT1

Conductor

Conductor count: 10 Gauge: 28 AWG, 0.089 mm² Material: tinned copper strands Stranding: ϕ 0.127 x 7 Resistance at 20 °C: 240 ohm/km maximum

Insulator

Material: SRPVC, 80 °C Color: black, white, red, yellow, blue, green, orange, purple, gray, brown Outer diameter: $Ø0.95 \pm 0.10$ mm Thickness: 0.23 mm minimum average Style: UL 1061

Outer jacket

Material: PVC, 80 °C Color: gray Diameter: ϕ 5 ±0.30 mm Thickness: 0.76 mm minimum average


Wire marking: E339579 UL AWM STYLE 2464 28AWG 80°C 300V VW-1 --- cUL AWM I A 80°C 300V FT1 TENSILITY

Tests

Tensile strength: 1.05 kgf/mm² After aging at 113 ±2 °C for 7 days: Minimum tensile strength 70 % original Minimum elongation 65 % original Flexibility: no observed cracking Heat shock: $121 \pm 1 \degree C / 1$ hour, no observed degradation Deformation: $121 \pm 1 \degree C / 1 hour, \le 50 \%$ Cold bend: -10 ± 2 °C /1 hour, no observed cracking Dielectric: 2000 Vac for 1 minute without breakdown

Use:

Internal wiring or external interconnection of electronic equipment



REVISION A	DATE 10/13/2015	DESCRIPTION Initial release	PREPARED: AG 2016.01.26 14:16:13 -08'00'	NOTES RoHS and REACH compliant		TENSILITY			
A1	1/26/2016	Updated dimensions	VERIFIED: LA Discrit/somety.la discrit/somety.la Discrit/somety.la	Function test: no open, no short circuit, no intermittent Meets UL appliance wiring standard 758		20802 Sockeye Place #130 Bend, OR 97701 USA tel 541.323.3228 fax 541.323.4202 800 877.670.7118 www.tensility.com			
			- MILLIMETERS TOLERANCES: X: ± 0.5 mm X.X: ± 0.3 mm X.XX: ± 0.05 mm	DESCRIPTION: Wire, 10C TS, 28 AWG, UL2464, 300V, 80C, 5.0 mm, VW-1, PVC, gray	SIZE A SCALE	30-0	NUMBER 10536	SHEET 1 OF 1	
		5	4	3	2				1