



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China




3M™ Thermally Conductive Acrylic Interface Pad 5590H

Product Description

3M™ Thermally Conductive Acrylic Interface Pad 5590H is a soft acrylic based pad designed to provide a preferential heat transfer path away from heat generating components. Because of its softness, 3M Interface Pad 5590H can decrease the load to integrated circuit chips during compression, and provides good tack to many surfaces. These properties lead to a high performance non-silicone based thermal pad. 3M Interface Pad 5590H is a higher thermal conductivity and somewhat firmer acrylic thermal pad, versus 3M Interface Pad 5589H.

- Good softness and conformability to non-flat surfaces.
- Excellent compressive stress relaxation.
- High thermal conductivity.
- UL94 V-0 certified (File No. E176845).
- Good surface tack leads to low thermal resistance at surface.
- Non-silicone acrylic elastomer.
- Good dielectric performance.
- Excellent durability for long term thermal conductivity and electric insulation stability.

Product Construction



Film liner (Roll type: Film on firm layer)
 Thermally conductive firm acrylic elastomer (very low tack) surface
 Thermally conductive soft acrylic elastomer (low tack) core

Dielectric Data

	100MHz		500MHz		1GHz	
	Dielectric constant ϵ	Dielectric tangent $\tan \delta$	Dielectric constant ϵ	Dielectric tangent $\tan \delta$	Dielectric constant ϵ	Dielectric tangent $\tan \delta$
5590H						
1.0mm t	5.7	0.03	5.5	0.024	5.4	0.024

Typical Physical Properties and Performance Characteristics

Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Property	Method	Value 3M™ Thermally Conductive Acrylic Interface Pad 5590H
Color	—	Light grey / White
Thickness (mm)**	5 mm dia. dial gauge	0.5 / 1.0 / 1.5
Thermal Conductivity (W/m-K)	3M method	3.0
Flammability	UL94	V-0
Density (g/cm ³ , @ 25°C)	JIS K6249	2.1
Hardness	Asker C Shore 00*	30 (data for conformable layer) 60
Volume Resistivity (Ω-cm)	JIS K6249	2.7 x 10 ¹²
Dielectric Strength (kV/mm)	JIS K6249	33

Note: *Shore 00 test method results are based on a 6mm thick sample. Results will vary with sample thickness. Sample tested to soft layer side of the pad.
**Tolerances of 1 mm and 1.5 mm = +/-10%, 0.5 mm +/- 0.1 mm.

3M™ Thermally Conductive Acrylic Interface Pad 5590H

Heat Stability

Duration (hrs)	Initial	500	1000	2000
Thermal Conductivity (W/m-K)	3.0	3.0	3.0	3.0
Hardness (Asker C)	30	33	33	34
Appearance	—	No effect	No effect	No effect

Aged at 110°C in high temperature chamber.

3M™ Thermally Conductive Acrylic Interface Pad 5590H	
UL Rating	In Service Temperature Resistance
UL94 V-0	Short Term (Hours-Days) 110-130°C
	Long Term (Weeks-Months) 90-100°C

Shelf Life

3M™ Thermally Conductive Acrylic Interface Pad 5590H shelf life is 12 months from date of manufacture when stored at room temperature conditions (20-25°C & 50%RH) and in the products original packaging.

An attribute of the product that can vary with storage is the cosmetic appearance of the material. Slight yellowing may occur and is considered normal for these type of products. Within the shelf life period, liner release can gradually change and should be considered to ensure robust end use and processing. Gradual liner release changes that are within the liner release specification for the shelf life period noted are typical for these products.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



Electronics Materials Solutions Division

3M Center, Building 225-3S-06
St. Paul, MN 55144-1000
1-800-251-8634 phone
651-778-4244 fax
www.3M.com/electronics

3M is a trademark of 3M Company.
Please recycle.
©3M 2014. All rights reserved.
60-5002-0672-1

