



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



Description

The 422B *Silicone Modified Conformal Coating* is a clear and flexible coating that is ideal for protecting electronic circuits in high temperature environments or applications requiring extreme flexibility. It protects against moisture, dirt, dust, and other particulates, and thus avoids corrosion of electronic components. It also insulates against high-voltage arcing, shorts, and static discharges. As well, it protects against thermal shock and puts very little stress on components during temperature cycling.

Compared to other typical silicones, the 422B is a one-part, acrylated silicone which makes it is easier to apply, remove, and rework. Also, it has a faster cure time and a much longer shelf life. It is available in both aerosol, liquid, and pen form and may be applied by spraying, dipping, or brushing.

The 422B protective coating is UL certified under the *Coatings for Use on Recognized Printed Wiring Boards—Component* category. It performs as a 94V-0 non-flammable coating. It is intended as an easy-to-use, cost-effective solution for protection against the typical risks PCB's face in high temperature environments. It is not intended for high voltage applications (>1500 V) with extended exposures (days) to very high humidity (>95%) and temperature environments (>65 °C [149 °F]). Customers with such applications should inquire about our line of silicone conformal coatings from Momentive Performance Materials.

Applications & Usages

The 422B improves reliability and lengthens the life of electronic circuitry. Its primary applications are in the automobile, marine, aerospace, aviation, communication, instrumentation, and industrial control equipment industries that involve high temperatures.

Benefits and Features

- **Certified flammability rating of *UL 94V-0*** (File # [E203094](#))
- **Maximum constant service temperature of 200 °C**
- **Fast drying time**—tack free in 7 min at room temperature; dries in 20 min at 65 °C
- **Protects electronics** from moisture, corrosion, fungus, thermal shock, and static discharges
- **Easy to inspect:** fluoresces blue at 437 nm ±65 nm under UVA light
- **Extended shelf life** avoids worries about premature hardening and wastage
- **Easy rework and repairs:**
 - Solders through the coat
 - Removable with Cat. No. 435 thinner



Usage Parameters

<i>Properties</i>	<i>Value</i>
Tack Free	5-7 min
Shelf life	5 y
Drying Time @20 °C [68 °F]	48 h
Drying Time @65 °C [149 °F]	20 min
Theoretical HVLP Spray Coverage ^{a)}	≤61 800 cm ² /L ≤6.18 m ² /L ≤9 580 in ² /gal ≤67 ft ² /gal

a) Idealized estimate based on a coat thickness of 25 µm [1.0 mil] and 100% transfer efficiency

Temperature Ranges

<i>Properties</i>	<i>Value</i>
Constant Service Temperature	-40 to 200 °C [-40 to 392 °F]

Principal Components

Name	CAS Number
Silicone and acrylic resin combination	<i>proprietary</i>
Xylene	1330-20-7
Acetone	67-64-1
Ethyl benzene	100-41-4

Cured 422B Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Color	Visual	Clear
Solderability	—	Fair
Flexibility	—	Excellent
Flammability	UL File # E203094	94V-0
UV inspection absorption max	Absorption spectrum	375 nm (near UV)
fluorescence max	Emission spectrum	437 nm (blue)
<i>Electrical Properties</i>	<i>Method</i>	<i>Value</i>
Dielectric Strength @0.0150"	IPC-TM-650 Test 2.5.6.1	1 056 V/mil
Volume Resistivity @23 °C 50% RH	ASTM D 257-07	1.2 x 10 ¹⁵ Ω·cm
Surface Resistivity	"	4.5 x 10 ¹⁶ Ω/sq
Dielectric Constant @60 Hz, 25 °C [77 °F]	ASTM D 150-98	2.35
Dielectric Constant @1 MHz, 25 °C [77 °F]	"	1.99
Dissipation Factor @60 Hz, 25 °C [77 °F]	"	0.037
@1 MHz, 25 °C [77 °F]	"	0.012

<i>Thermal Properties</i>	<i>Method</i>	<i>Value</i>	
Coefficient of Thermal Expansion (CTE)	IPC-TM-650 Test 2.4.24	253 ppm/°C	
Glass Transition Temperature (T _g)	"	None detected	
Softening Point	"	31 °C [88 °F]	
<i>Environmental & Ageing Study</i>	<i>Method</i>	<i>Value</i>	
Salt Spray Test: 7 day @35 °C +Salt/Fog	ASTM B117-2011	5B = 0% area removed	
Cross-hatch adhesion	ASTM D3359-2009		
Cracking, unwashed area	ASTM D661-93		None
Visual Color, unwashed area	ASTM D1729-96		No change
Peeling, unwashed area	"		None

Uncured 422B Properties

<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Odor	—	Ethereal
Viscosity @23 °C [73 °F]	Brookfield SP1	60 cP [0.060 Pa·s]
Density		0.898 g/mL
Flash Point	Closed Cup	-18 °C [-0.40 °F]
Boiling Point		55 °C [131 °F]
Solids Content (w/w)		28%

Compatibility with Substrate

The 422B silicone is compatible with most materials found on printed circuit assemblies; however, in an uncured state it is not compatible with contaminants like water, oil, and greasy flux residues. Therefore, it is extremely important to clean the printed circuit assembly thoroughly with a suitable electronic cleaner before applying the coating.

The chosen electronic cleaners should remove moisture, wax, greases, oils, and all other contaminants that are known to cause defects in this type of conformal coating (see recommended cleaners on page 5).

Health, Safety, and Environmental Awareness

Please see the 422B **Safety Data Sheet** (SDS) for more details on transportation, storage, handling and other security guidelines.

Environmental Impact: The 422B formulation is free from ozone depletion compounds. The coating is RoHS compliant.


Health and Safety: The liquid is flammable and should be kept away from flames and other ignition sources. As with most paint materials, avoid breathing in fumes or direct contact with the material. Solvents therein can cause irritation and other symptoms like headaches, pain, as well as having long term exposure effects. The cured coating presents no known hazard.

Wear safety glasses and disposable nitrile gloves for short contact (<4 hours). For extended contact use Viton gloves. Wash hands thoroughly after use. Use in the open air, in fume hoods, or in well ventilated area. For short or long term (8 hours) at levels of exposures exceeding 100 ppm xylene or 750 ppm acetone, use NIOSH approved respirator with organic vapor cartridges rated for this order of concentrations.

HMIS® RATING

HEALTH:	* 2
FLAMMABILITY:	3
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Spray Gun Application Instructions

Read the procedure below and make necessary adjustments according to your spray gun equipment usage instructions.

Thinning Requirements

Let down is not required for 422B and will usually lead to a dry film thickness of roughly 1 mil [25 µm] in one coat (depending on the operator). When diluted 1:1, each coat results in a dry film thickness of roughly 0.5 mil [13 µm].

If higher solid percent grade or custom blends are used, contact us for details.

ATTENTION! MG Chemicals recommends a dry film thickness of 25 to 38 µm [1 to 1.5 mil]. Since it is a solvent-based and acrylated silicone system, the thickness upper limit is below 75 µm [3 mil]. The usual limits for solvent-less silicone systems that have thermosetting cure mechanisms do not apply.

Spray Equipment

Use a HVLP (high-volume, low pressure) spray gun using the initial settings described in the following table. Adjust these settings and recommendations as required.

Initial Setting Recommendations

Air Cap	#3 HVLP		
Pressure	<i>Inlet</i> 23 psi	<i>Air flow</i> ^{b)} 13.5	<i>Air cap</i> 10 psi
Fluid Tip	1.3 mm [0.051"]	1.5 mm [0.059"] ^{a)}	

Note: These recommendations are based on a generic paint gun and may differ by brands. Please consult your spray gun manufacturer's guide.

- a) If no or reduced let down is performed, this may be a better tip choice.
- b) SCFM = standard cubic foot per minute

To apply the required thickness

- Mix the paint thoroughly with a paint shaker, mixer, or spatula.
- Dilute by a ratio of **1:1** (Paint:Thinner) or another ratio of your choice.
- Make a test spray. Adjust the spray settings for best flow and spray quality, and establish an appropriate distance to avoid paint runs. A distance between 23 to 30 cm (9 to 12 in) is recommended.
- Spray a thin and even coat onto the vertical surface to be coated. For best results, start your movement off-surface, press the trigger, and only release off-surface at the end of the stroke. Use a uniform movement of the spray gun parallel to the surface.
- Wait at least 5 minutes and spray another coat. This delay avoids trapping solvent between coats.
- Rotate the board 90° to ensure good coverage.
- Apply additional coats until desired thickness is achieved (go to Step 3).
- Let dry for 7 minutes (flash off time) at room temperature.

ATTENTION! Spraying overly thick coats may cause paint runs and hamper solvent evaporation. Prefer the application of many thin wet coats rather than fewer heavy coats.

Pen Application Instructions

Follow the procedure below for best results.

To apply the liquid pen

- Ensure that the surface to be coated is clean and oil-free.
- Shake the pen vigorously.
- Test on a blank to ensure good flow quality and uniformity during application.
- Touch the pen lightly on the surface while squeezing the barrel to apply thin and even coat.
- Let dry for 3-5 minutes (flash off time) at room temperature before handling.

To cure the conformal coating

- Full cure can be achieved in 48 hours at room temperature.
- Full cure can be achieved in 20 minutes by using an infrared lamp or in convection oven at 65 °C [149 °F].

Note: The procedure above is based on a minimum thickness of 25 µm [1 mil] conformal coating. After full cure, measure the actual conformal coating thickness to ensure it meets the applications requirements. Custom cure instructions are required for higher thicknesses (contact us for details).

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Packaging</i>	<i>Net Volume</i>		<i>Net Weight</i>		<i>Packaging Weight</i>	
422B-55ML	Bottle	55 mL	1.8 fl oz	49 g	1.7 oz	1.0 kg	2.1 lb ^{a)}
422B-1L	Can	945 mL	2 pt	848 g	1.87 lb	5.2 kg	11 lb ^{a)}
422B-4L	Can	3.78 L	1 gal	3.39 kg	7.48 lb	3.8 kg	8.3 lb
422B-20L	Pail	18.9 L	5 gal	16.9 kg	37 lb	20 kg	45 lb
422B-P	Pen	5 mL	0.16 fl oz	4.4 g	0.15 oz	0.02 kg	0.04 lb
422B-340G	Aerosol	425 mL	14 fl oz	340 g	12 oz	4.6 kg	10 lb ^{b)}
422B-340GCA	Aerosol	425 mL	14 fl oz	340 g	12 oz	4.6 kg	10 lb ^{b)}

Contact MG Chemicals if custom packaging or sizes are required

a) Pack of five bottles

b) Pack of ten cans

Thinners & Conformal Coating Removers

- *Thinner 2*: Cat. No. 4352-945ML, 4352-4L (1 gal), 4352-20L, 4352-200L
- *Conformal Coating Stripper—Liquid*: Cat. No. 8312-580ML, 8312-3.78L

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

+ (44) 1663 362888 (UK & Europe)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.