



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



SPECIFICATION CONTROL DRAWING

44A0211

TITLE WIRE, RADIATION-CROSSLINKED, POLYALKENE-INSULATED, LIGHT WEIGHT, GENERAL PURPOSE, 1000 VOLT

Date 24MAR11

Revision K1

This specification sheet forms a part of the latest issue of Raychem Specification 44 and MIL-W-81044 as applicable.




TABLE I. CONSTRUCTION DETAILS

PART NUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	MAXIMUM DIAMETER STRANDED CONDUCTOR (in.)	FINISHED WIRE		
				MAXIMUM RESISTANCE AT 20°C (ohms/1000ft.)	DIAMETER (in.)	MAXIMUM WEIGHT (lbs/1000 ft.)
44A0211-26-*	26	19 x 38	.021	41.3	.040 ± .002	1.6
44A0211-24-*	24	19 x 36	.026	26.2	.046 ± .002	2.4
44A0211-22-*	22	19 x 34	.033	16.2	.054 ± .002	3.5
44A0211-20-*	20	19 x 32	.041	9.88	.062 ± .002	5.1
44A0211-18-*	18	19 x 30	.051	6.23	.073 ± .003	7.7
44A0211-16-*	16	19 x 29	.058	4.81	.081 ± .003	9.8
44A0211-14-*	14	19 x 27	.073	3.06	.098 ± .004	14.7
44A0211-12-*	12	37 x 28	.090	2.02	.117 ± .004	22.1
44A0211-10-*	10	37 x 26	.114	1.26	.146 ± .004	35.6
44A0211- 8-*	8	133 x 29	.173	.701	.206 ± .006	61.8
44A0211- 6-*	6	133 x 27	.217	.445	.254 ± .007	94.5
44A0211- 4-*	4	133 x 25	.274	.280	.308 ± .008	150.

TABLE II. PERFORMANCE DETAILS

PART NUMBER 1/	BEND TESTING				
	MANDREL DIAMETER (inch) (± 3%)			WEIGHT (lb) (± 3%)	
	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND
44A0211-26-*	.500	.750	.250	.375	1.00
44A0211-24-*	.500	1.00	.250	.375	2.00
44A0211-22-*	.750	1.00	.250	.375	2.00
44A0211-20-*	.750	1.00	.250	.500	3.00
44A0211-18-*	1.00	1.50	.375	.500	3.00
44A0211-16-*	1.00	1.50	.375	1.00	4.00
44A0211-14-*	1.50	2.00	.500	1.00	4.00
44A0211-12-*	2.00	2.00	.500	1.50	4.00
44A0211-10-*	3.00	3.00	.750	2.00	4.00
44A0211- 8-*	3.00	4.00	.750	3.00	5.00
44A0211- 6-*	4.00	5.00	1.00	3.00	8.00
44A0211- 4-*	5.00	6.00	1.25	3.00	8.00

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.



TE Connectivity
Wire & Cable
501 Oakside Avenue
Redwood City, CA 94063-3800
Phone: 1-800-227-8816
Fax: 1-650-361-6297

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature

VOLTAGE RATING: 1000 volts (rms) at sea level

ACCELERATED AGING: 300 ± 2°C for 6 hours

Identification legibility, 225 ± 2°C for 6 hours

BLOCKING: 150 ± 2°C for 24 hours

COLOR: White preferred

FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum);

no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance, 5000 megohms for 1000 ft. (minimum)

IDENTIFICATION AND STRIPING DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Elongation, 150% (minimum)

Tensile Strength, 2500 lbf/in² (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 2.0 kV (rms)

Impulse Dielectric Test, 6.0 kV (peak)

Finished Wire;

Spark Test, 4.0 kV (rms) at 3 kHz

Impulse Dielectric Test, 8.0 kV (peak)

INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

LIFE CYCLE: 200 ± 2°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours

SHRINKAGE: 300 ± 2°C, 0.125 in. (maximum) in 12 in., AWG 26-12

300 ± 2°C, 0.250 in. (maximum) in 12 in., AWG 10-4

SMOKE: 200 ± 2°C, No visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK RESISTANCE: 150 ± 2°C, 0.060 in. (maximum)

VOLTAGE WITHSTAND TEST (Post Environmental): 3000 volts (rms), 60 Hz, 5 minutes

WICKING: 2.25 in. (maximum)

PART NUMBER: The "*" in the part numbers on page 1 shall be replaced by color code designators.

1/ Example: AWG 20, white: 44A0211-20-9

1/ See footer section on page 1