

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com


Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China











## **BAG, DISSIPATIVE PINK POLY**

Meets ANSI/ESD S20.20, Packaging standard ANSI/ESD S541, and Static Control Bag ANSI/ESD S11.4 Level 5

**Specifications:** 

Electrical PropertiesTypical ValueTest Procedures/MethodStatic Decay:< 1.0 sec.</td>ASTM 101 Method 4046Surface Resistance:1 x 104 to < 1 x 1011 ohms</td>ANSI/ESD STM11.11Polycarbonate Haze:NE72 hr contactCorrosivity Observations:NEMIL-STD-3010, M3005

**Physical Properties** 

Material Thickness: 4.0mils (0.004", 0.1016mm), +/- 10%

 Melt Index:
 0.050 gm/ 10 min
 ASTM D-1283

 Density:
 0.923 gm/cc
 ASTM D-1505

 Dart Impact:
 230 gms
 ASTM D-1709

Coefficient of Friction: MD 24,000 psi ASTM D-1894 (unmodified film)

1% Secant Modulus (Stiffness): MD 25,000 psi ASTM D-882

Per ANSI/ESD S541 section 6.1 Inside an ESD Protected Area "Packaging used within an EPA (that satisfies the minimum requirements of ANSI/ESD S20.20) shall be:

- Low charge generation.
- Dissipative or conductive materials for intimate contact."

## **RoHS 2 and REACH Statement**

None of the RoHS 2 restricted materials or REACH substances of very high concern as of 2013-12-16 are intentionally added in manufacturing this product. Ref: European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Protektive Pak Limited Warranty at ProtektivePak.com.



Specifications are subject to change without notice.



Dimensional tolerances unless otherwise specified: L: +/- 0.250" / W: +/- 0.250"

## PROTEKTIVE PAK

TRANSPARENT STATIC DISSIPATIVE (PINK POLY)

PROTEKTIVE PAK
13520 MONTE VISTA AVENUE, CHINO, CA 91710
PHONE (909) 627-2578
ProtektivePak.com

DRAWING NUMBER 49100 DATE March 2015