



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts,Customers Priority,Honest Operation,and Considerate Service",our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





1120 Tape

Aluminum Foil with Conductive Adhesive

Data Sheet



Product Description

3M™ 1120 Tape consists of a 1-ounce deadsoft aluminum foil backing and an electrically conductive pressure-sensitive acrylic adhesive.

- Deadsoft 1-ounce aluminum foil backing
- Conductive acrylic adhesive
- Supplied on a removable liner for easy handling and diecutting
- Meets flame spread requirement of UL 510

Applications

3M 1120 tape is typically used for applications requiring excellent electrical conductivity and is designed for EMI/RFI shielding and cable wrap.

Shielding Effectiveness

Many factors determine the true shielding effectiveness of a shielding tape, including type and thickness of foil, adhesive type, intimacy of contact, smoothness of application surface, strength and frequency of the EMI signal, etc. However, using standard tests and fixtures, it is possible to determine a value for the attenuation.

Typical Properties

Typical Values

Adhesive	Acrylic Conductive
Backing	Aluminum
Backing Thickness	2.0 mils (0.05mm)
Total Thickness ¹	4.0 mils (0.100mm)
Color	Silver Metallic
Electrical Resistance ²	0.009 ohm
Flame Retardancy ³	Pass
Breaking Strength ⁴	16 lbs/in (25N/10mm)
Elongation ⁴ (% at break)	5%
Adhesion to Steel ⁵	36 oz/in (3.9N/10mm)

Note: Typical properties are not recommended for specification purposes. Product specifications will be provided upon request.

Footnote: 1 Test Method ASTM D1000

2 Mil-STD-202 Method 303 maintained at 5 psi (3,4N/cm²) measured over 1 in² surface area. Conductive particles in the adhesive provide the electrical path between the application substrate and the foil backing.

3 UL Recognized for flame retardancy per UL 510, Product Category OANZ2, File E17385.

4 Test Method ASTM D3759

5 Test Method ASTM D3330

3M is a trademark of 3M

IMPORTANT NOTICE

Before using this product, you must evaluate it and determine if it is suitable for your intended application. You assume all risks and liability associated with such use.

Warranty; Limited Remedy; Limited Liability. This product will be free from defects in material and manufacture as of the date of purchase. **3M MAKES NO OTHER WARRANTIES INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** If this product is defective within the warranty period stated above, your exclusive remedy shall be, at 3M's option, to replace or repair the 3M product or refund the purchase price of the 3M product. **Except where prohibited by law, 3M will not be liable for any loss or damage arising from this 3M product, whether direct, indirect, special, incidental or consequential regardless of the legal theory asserted.**



Electrical Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
<http://www.3M.com/elpd/oem>

Litho in USA.
© 3M IPC 2001 78-8125-9944-3-A