



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





UHMW Polyethylene Tape

5421 · 5423

Technical Data

July, 2016

Product Description 3M™ UHMW Polyethylene Tapes are film coated with a rubber adhesive which provides an excellent abrasion resistant surface. These tapes feature a unique combination of properties that make it ideal for many tough impact wear or sliding applications. 3M™ UHMW-PE Film Tape 5421 is a thinner version of 3M™ UHMW-PE Film Tape 5423.

Product Construction	Backing	Adhesive	Color	Standard Roll Length
	UHMW-PE Film (ultra-high molecular weight polyethylene)	Rubber	Translucent	36 yds. (32.9 m)

Typical Physical Properties **Note: The following technical information and data should be considered representative or typical only, and should not be used for specification purposes.**

		ASTM Test Method
3M tape 5421		
Adhesion to Steel:	34 oz./in. width (37 N/100 mm)	D-3330
Tensile Strength:	46 lbs/in. width (796 N/100 mm)	D-3759
Elongation at Break:	470%	D-3759
Backing Thickness:	5.0 mils (0.13 mm)	D-3652
Total Tape Thickness (without liner):	6.7 mils (0.17 mm)	D-3652
Liner Thickness:	3.5 mils (0.09 mm)	D-3652
Temperature Use Range:	-30° to 225°F (-34° to 107°C)	
3M tape 5423		
Adhesion to Steel:	36 oz./in. width (39 N/100 mm)	D-3330
Tensile Strength:	86 lbs/in. width (1500 N/100 mm)	D-3759
Elongation at Break:	530%	D-3759
Backing Thickness:	10 mils (0.25 mm)	D-3652
Total Tape Thickness (without liner):	12 mils (0.30 mm)	D-3652
Liner Thickness:	3.5 mils (0.09 mm)	D-3652
Temperature Use Range:	-30° to 225°F (-34° to 107°C)	

Features

- Tape demonstrated no evidence of wear through after Taber Abrasion at 1000 cycles, using CS-10 wheel and 1000g load when applied to S-37 mounting sheet.
- Low water vapor transmission rate <0.50 g/100in.²/24hrs.
- Thick caliper UHMW polyethylene tape for extended service life as a protective surface against tough impact wear or sliding applications.
- Outstanding abrasion resistance so will outwear PTFE and other materials in sliding applications.
- Low coefficient of friction characteristics is exceeded only by PTFE.
- UHMW-PE tape can be used where lubrication is not possible because of contamination.
- Rubber Adhesive provides good initial tack for immediate bonding to material surface.
- Liner makes it ideal for fabricating or die-cutting into various lengths and shapes.

Application Ideas

- Noise reduction between dissimilar parts.
- Reduce squeaks, rattles and other noises that occur with movement
- Lining of conveyer guide rails, tank and bin liners, and discharge chutes.
- Protection for aluminum sheets on stretch forming presses.
- Liners for Spray booths.
- Slick surface for easy glide for drawers and cabinets.

Storage

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity in the original packaging material.

Shelf Life

To obtain best performance, use this product within 18 months from date of manufacture.

Technical Information

The technical information, recommendations and other statements contained in this document are based upon tests or experience that 3M believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Product Use

Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. Given the variety of factors that can affect the use and performance of a 3M product, user is solely responsible for evaluating the 3M product and determining whether it is fit for a particular purpose and suitable for user's method or application.

Warranty, Limited Remedy, and Disclaimer

Unless an additional warranty is specifically stated on the applicable 3M product packaging or product literature, 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY OR CONDITION ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. If the 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability

Except where prohibited by law, 3M will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

ISO 9002

This Industrial Adhesives and Tapes Division product was manufactured under a quality system registered to ISO 9001:2000 standards.

3M

Industrial Business
Industrial Adhesives and Tapes Division
3M Center, Building 220-3S-06
St. Paul, MN 55144-1000
3M Company.
800-362-3550 · 577-369-2923 (Fax)
www.3M.com/industrial

Recycled Paper

*40% pre-consumer
10% post-consumer*

3M is a trademark of

Printed in U.S.A.
©3M 2016