



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!




## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





## 5744 Solder Saver®

---

### Product Description

Kester 5744 Solder Saver® is a chloride-free, inorganic white powder formulated to remove dross, the oxide of solder, from still solder pots and wave soldering machines. Unlike most active reducing materials, 5744 does not decompose to sticky residues that are harder to remove than the original dross. 5744 has been designed to be low fuming and is stable at soldering temperatures and has been shown to be effective up to 380°C (720°F). This makes the 5744 a good candidate for both tin-lead and lead-free solder baths. Unlike flammable, messy, organic-based solder cover chemicals, 5744 is a non-flammable powder that remains a solid while it is working and is easily removed from the solder pot after it is used. Reducing tin oxide back to tin metal will greatly reduce dross scrap and will help keep the soldering pot surface clear of residues.

### Physical Properties

**Appearance:** White Crystals

**Melting Point:** Sublimes >300°C

**Flash Point:** None

### Application

5744 must be used on a still solder pot surface. All solder wave pumping and agitation action must be turned off. The pot temperature should be controlled to 232-260°C (450-500°F). Cover the solder surface with 5744 by sprinkling the powder on the pot in a thin covering layer, no greater than 6.4mm (0.25in) thick. Slowly mix the salt with the surface of the solder with a metallic solder ladle or a metal spatula. Allow the salt 10 seconds after mixing to convert the dross back to solder. Move any dross on the pot into the salt covered surface to convert the dross to metal. When done, remove the dross recovery salt and other dirt residues with a metallic solder ladle or a metal spatula. All of the 5744 should be removed from the solder surface. 5744 is intended to be used as received.

### Storage, Handling and Shelf Life

5744 should be stored in sealed containers. Shelf life is 3 years from date of manufacture when handled properly and held at -10-45°C (14-113°F).

### Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at <https://www.kester.com/downloads/sds>.