



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



(10 X 24)"

Fyberoid "Fish Paper"

560



Specifications:

- *Size: 10" wide*
- *Description: Vulcanized Cellulose Fiber*
- *Color: Blue-Grey*
- *Thickness: 0.010 inch ± 10%*
- *Uses: All electrical insulation*
- *Tensile Strength: MD 15,000 psi, (typical)*
CD 6,000 psi, (typical)
- *Density: 1.1 gram per cubic centimeter min.*
- *Electrical Strength: 300 Volts per mil (typical)*
- *Bursting Strength: (Mullen) 270 psi, (typical)*
- *Tearing Strength: MD 375 grams, (typical)*
CD 450 grams, (typical)
- *Zinc Chloride Content: 0.05% max.*

- *Meets Mil. Spec. MIL-I-695A Type F.*

Rolled

Cat. No. 560

Flat/100 Pack

Cat. No. 560-100

Also, # 562-4048 for (40 x 48) in.

#560 Thin Insulated "Fish Paper". For numerous repair jobs around the shop where electrical insulation is required. Its qualities of toughness, flexibility, and edge-tearing resistance, combined with high dielectric strength, and ready absorption of insulating varnish, have led to its predominant use as an IMPROVED motor slot call insulation.