



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





63 Tape

PTFE Film With Acrylic Adhesive

Data Sheet

Product Description

- 2.0-mil PTFE backing
- Acrylic adhesive
- Supplied on 3 inch cores

Like all 3M insulating tapes, 3M™ 63 Tape is available in standard and custom widths and lengths. Standard length is 36 yards.

- Widths from 1/4" to 13"
- Longer lengths up to several times normal length, dependent upon width. Check with Customer Service.

Applications

3M 63 Tape is for use on coils, capacitors and wire harnesses; solvent-resistant adhesive; for use where chemical properties are more important than temperature resistance.

Properties

Typical Values

Adhesive	Acrylic
Backing	PTFE Film
Backing Thickness ¹	2.0 Mil
Total Thickness	3.5 mils/0.088mm
Temperature Class	155°C /307°F
Dielectric Breakdown ¹	9500 Volts
Insulation Resistance ¹ (megohms)	>1 x 10 ⁶
Breaking Strength ¹	20 lbs./in. (35 n/10mm)
Elongation ¹ (% at break)	200
Electrolytic Corrosion Factor ²	1.0
Adhesion to Steel ¹	35 oz./in. (3.8 n/10mm)
UL Flame Retardant ³	Yes

* Footnote: 1. Test method ASTM D 1000
2. 3M Test Method-Available on request
3. UL-recognized for flame retardancy per UL 510, Product Catagory 0ANZ2, File E17385.

3M is a trademark of 3M.

Important Notice

All statements, technical information and recommendations related to the Seller's products are based on information believed to be reliable, but the accuracy or completeness thereof is not guaranteed. Before utilizing the product, the user should determine the suitability of the product for its intended use. The user assumes all risks and liability whatsoever in connection with such use.

Any statements or recommendations of the Seller which are not contained in the Seller's current publications shall have no force or effect unless contained in an agreement signed by an authorized officer of the Seller.

The statements contained herein are made in lieu of all warranties, expressed or implied, including but not limited to the implied warranties of merchantability and fitness for a particular purpose which warranties are hereby expressly disclaimed.

SELLER SHALL NOT BE LIABLE TO THE USER OR ANY OTHER PERSON UNDER ANY LEGAL THEORY, INCLUDING BUT NOT LIMITED TO NEGLIGENCE OR STRICT LIABILITY, FOR ANY INJURY OR FOR ANY DIRECT, INDIRECT, SPECIAL, INCIDENTAL OR CONSEQUENTIAL DAMAGES SUSTAINED OR INCURRED BY REASON OF THE USE OF ANY OF THE SELLER'S PRODUCTS THAT WERE DEFECTIVE.



Electrical Products Division

6801 River Place Blvd.
Austin, TX 78726-9000
800-676-8381
<http://www.3m.com/elpd>

© 3M 1998
78-8124-4717-1