

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



# Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832


Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China









## BLUE, DARK GREY, BEIGE, DARK BLUE

#### Disclaimer:

All statements, technical data, and recommendations contained herein are based upon tests we believe to be reliable. However, the accuracy or completeness thereof is not guaranteed. The proper and correct applications of products and data is the responsibility of the user. Statements or recommendations not contained herein shall have no force or effect unless embodied in a written agreement signed by authorized offers of Desco Industries, Inc.

#### Tolerances:

Width +/- .250"

Length +/- .250" every 1 linear foot of running material.

See reverse side for available mat and roll sizes.



## **Description:**

Statfree® Type T2 meets the worksurface requirements of ANSI/ESD S20.20 and EIA-625. This material is a dual purpose rubber matting material. The two layer construction allows it to be used as a dissipative or a conductive matting product. The soft dissipative layer makes an excellent table mat, ideal for use in soldering and assembly areas. This rubber material has superior resistance to heat, abrasion, chemicals, and is easy to clean and maintain. Statfree® Type T2 material will not melt and does not burn when coming into contact with hot metal parts or soldering debris. It is amine, chloride, sulfide, alumina, and magnesia free. Statfree® Type T2 is suitable for use with continuous monitors.

Statfree® Type T2 is manufactured without any ozone depleting substances, and in accordance with the Montreal Protocol.

## **Electrical Properties:**

<u>Property</u> <u>Test Method</u> <u>Value</u>

RTT Resistance: ESD S4.1 10<sup>6</sup> - 10<sup>8</sup> Ohms RTG Resistance: ESD S4.1 10<sup>6</sup> - 10<sup>8</sup> Ohms Charge Decay: FTMS 101C, Method 4046 0.01seconds

Electrical Properties obtained by testing to industrial standards by an independent testing laboratory @ 100 Volts and 50% relative humidity unless otherwise specified. Complete text of the test report is available upon request.

## **Specifications:**

Construction: Dual-layer rubber material

Thickness: 0.060" (1.5mm)

Color:\* Blue, Dark Blue, Dark Grey, Beige (top), Black (bottom)

Texture:\* Slight embossed

Weight: 0.43 lbs./sq. ft. (0.2g/cm<sup>2</sup>)

Hardness:  $65 \pm 5$  Shore "A", per ASTM-D2240

Heat Resistance: Does not melt or burn when coming into contact with hot solder and soldering irons.

Chemical Resistance: Resistance to degradation by inorganic acids, organic acids, reducing agents, aliphatic hydrocarbons,

mineral oil, aldehydes, and amines

\*Color and texture may vary between lots and mills

<u>Grounding:</u> This material must be properly grounded for optimum electrical performance. Ask for Technical Bulleltin TB-2000 for mat grounding instructions.

<u>Cleaning:</u> Use only ESD mat cleaner such as Reztore<sup>™</sup> Surface & Mat Cleaner to clean and extend mat useful life. Do not use cleaners containing silicone as silicone will create an insulative film on the surface. Do not sue solvent based cleaners as solvents will dry out matting and may cause curling.

# STATFREE® MATERIAL, DISSIPATIVE, RUBBER, 2-LAYER, 0.060" (1.5mm)



**DESCO WEST:** 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: www.desco.com PHONE (909) 627-8178 FAX (909) 627-7449

1110NL (303) 021-0170 TAX (303) 021-1443

**DESCO EAST:** 90 HUDSON RD, CANTON, MA 02021-1407 PHONE (781) 821-8370 FAX (781) 575-0172 MATERIAL TYPE T2

Limited Lifetime Warranty:

Desco warrants for one year that

Statfree<sup>®</sup> matting products will be free

the mat. Damage to matting caused by

of defects in materials and workman-

ship and will guarantee dissipative/conductive mat properties for the life of

misuse of any kind, including using

by Desco Limited Warranty.


inappropriate cleaners is not covered

DRAWING PM-104

**DATE:** 4/05

## Item Number Reference For Statfree® Type T2 Rubber, Dissipative, 2-Layer

# **KITS**



## **Mat Top Kit Item Numbers**

SIZE	BEIGE	BLUE	DK. GREY	DK. BLUE
24" x 36"	66030	66040	66050	66051
24" x 48"	66035	66045	66055	66056

### MAT TOP KIT INCLUDES

- 1 Benchmat, Type T2, size as specified
- 1 09826, common point ground cord
- 1 09864, universal snap kit



Look for the Statfree<sup>®</sup> brand on Desco
ESD matting. All Desco mat top kits are
permanently marked for your
protection and auditing purposes.


# **ROLL STOCK**




Type T2 Is Also Available In Full Rolls

#### Hardware is not included with rolls.

As a general rule, continuous runs of ESD matting should be grounded at ten-foot intervals to ensure path-to-ground and not substantially increasing RTG. Each individual ESD mat should be grounded with ground snap located no further than five feet from either end.







### **Roll Stock Item Numbers**

SIZE	BEIGE	BLUE	DK. GREY	DK. BLUE
24" x 40'	66060	66070	66080	66081
30" x 40'	66115	66110	66105	66106
36" x 40'	66065	66075	66085	66086
48" x 40'	66090	66095	66100	66101

Matting materials have a tendency to shrink slightly when first unrolled. In applications where length is critical, allow the material to relax for at least 4 hours before cutting to size. Always trim with a sharp knife or razor blade.