imall

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





HydroMark 531 Solder Paste Water-Soluble, Halide-Free

Product Description

Kester HydroMark 531 is a halide-free, organic acid, water-soluble solder paste that provides users with the highest level of consistency and performance. Batch after batch, HM531 provides hours of stable stencil life, tack time and repeatable brick definition. HM531's robust printing characteristics result in consistent solder paste volume regardless of idle time, stencil life and print speed. The activator package in the HM531 is very aggressive and provides superior wetting to OSP-coated PCB's and PdAg components. The outstanding batch consistency, anti-slump chemistry, consistent print volumes, solderability and cleanability make the HM531 an ideal water-soluble solder paste for any application.

Performance Characteristics:

- Outstanding batch-to-batch consistency
- Excellent anti-slump characteristics minimizing bridging defects
- Capable of 60+ minute idle times in printing
- Capable of print speeds up to 150mm/sec (6in/sec)

Standard Applications:

Stencil Printing and Enclosed Head Printing: 90% Metal

- Excellent solderability to difficult lead-free metalizations with a leaded paste
- Residues easily removed with hot DI water, even up to 8 hours after soldering as a best process practice
- Minimal foam in wash systems
- 8+ hour stencil life
- Classified as ORM0 per J-STD-004
- Produces minimal voiding underneath BGA components
- Compatible with enclosed print head systems

RoHS Compliance

Kester does not determine any applicable Restriction of Hazardous Substances (RoHS) exemptions for our lead containing products at the user level.

Physical Properties

Data given for Sn63Pb37, 90% metal, -325+500 mesh)

Viscosity (typical): 1800 poise Malcom Viscometer @ 10rpm and 25°C



Copper Mirror Corrosion: Low Tested to J-STD-004, IPC-TM-650, Method 2.3.2

Corrosion Test: Low Tested to J-STD-004, IPC-TM-650, Method 2.6.15

Silver Chromate: Pass Tested to J-STD-004, IPC-TM-650, Method 2.3.33 Initial Tackiness (typical): 43 grams Tested to J-STD-005, IPC-TM-650, Method 2.4.44

Slump Test: Pass Tested to J-STD-005, IPC-TM-650, Method 2.4.35 Solder Ball Test: Preferred Tested to J-STD-005, IPC-TM-650, Method 2.4.43

Wetting Test: Pass Tested to J-STD-005, IPC-TM-650, Method 2.4.45

Chloride and Bromides: None

Detected Tested to J-STD-004, IPC-TM-650, Method 2.3.35

Fluorides by Spot Test: Pass Tested to J-STD-004, IPC-TM-650, Method 2.3.35.1

Surface Insulation Resistivity (SIR) (typical): Pass

Tested to J-STD-004, IPC-TM-650, Method 2633

	Blank	HM531
Day 1	1.9*10 ¹⁰ Ω	1.4*10 ⁸ Ω
Day 4	1.1*10 ¹⁰ Ω	2.0*10 ⁸ Ω
Day 7	8.3*10 ⁹ Ω	8.3*10 ⁹ Ω

Global Headquarters: 800 West Thorndale Avenue, Itasca, IL USA 60143 • Phone: +1 800.2.KESTER • Fax: +1 630.616.4044 Asia-Pacific Headquarters: 61 Ubi Avenue 1 #06-01 UB Point, Singapore 408941 • Phone: +65 6.449.1133 • Fax: +65 6.242.9036 European Headquarters: Ganghofer Strasse 45, 82216 Gernlinden, Germany • Phone: +49 (0) 8142 4785 0 • Fax: +47 85 61 Asia Manufacturing: Hengqiao Road, Wujiang Economic Development Zone • Suzhou, Jiangsu Province, China 215200 • Phone: +86 512.82060807 • Fax: +86 512.8206 0808

Website: www.kester.com

Application Notes



Availability


HydroMark 531 is commonly available in the Sn63Pb37 and Sn62Pb36Ag02 alloys. Type 3 powder mesh is recommended, but different powder particle size distributions are available for standard and fine pitch applications. For specific packaging information see Kester's Solder Paste Packaging Chart for available sizes. The appropriate combination depends on process variables and the specific application.

OPrinting Parameters

Squeegee Blade	Stainless Steel or 80-90 Durometer Polyurethane
Squeegee Speed	Capable to a maximum speed of 150mm/sec (6 in/sec)
Stencil Material	Stainless Steel, Molybdenum, Nickel Plated or Brass
Temperature/Humidity	Optimal ranges are 21-25°C (70-77°F) and 30-70% RH

Recommended Reflow Profile

The recommended reflow profile for HM531 made with either the Sn63Pb37 or Sn62Pb36Ag02 is shown here. This profile is simply a guideline. Since HM531 is a highly active, water-soluble solder paste, it can solder effectively over a wide range of profiles. HM531 is capable of reflowing at the 235°C peak temperatures required for fully collapsing lead-free SAC BGA's for maximum reliability, and remains easy to clean after these high temperature profiles. Your optimal profile may be different from the one shown based on your oven, board and mix of defects. Please contact Kester Technical Support if you need additional profiling advice.



Cleaning

HM531 residues are best removed using automated cleaning equipment (in-line or batch) within 8 hours of soldering as a best process suggestion. De-ionized water is recommended for the final rinse. Water temperatures should be 49-60°C (120-140°F). Kester's 5768 Bio-Kleen[®] saponifier can also be used in a 1-2% ratio for aqueous cleaning systems if required for low clearance components. Call Kester Technical Support for details.

Storage, Handling and Shelf Life

Refrigeration is the recommended optimum storage condition for solder paste to maintain consistent viscosity, reflow characteristics and overall performance. HM531 should be kept at standard refrigeration conditions, 0-10°C (32-50°F). HM531 should be stabilized at room temperature prior to printing. It is recommended to be removed from refrigeration at least 4 hours prior to being opened and having solder paste placed on the stencil. All containers will have their covers on when material is not being removed from them. Jars will have the inner plunger pushed down to the level of the solder paste and the top screwed tight. Cartridges will have both lids on them and stored with the small tip down or on their sides, never with the large round end down. Contact Kester Technical Support if you require additional advice with regarding storage and handling of this material. Shelf life is 6 months from the date of manufacture when handled properly.

\otimes Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product.