



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



CHEMINAX


DATA BUS CABLE, OPTIMIZED DOUBLE SHIELD,
MULTIPLEX, MIL-STD-1553

Date: 8-31-88
Revision:

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

CONSTRUCTION DETAILS

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED. METRIC UNITS SHOWN IN PARENTHESES ARE APPROXIMATE EQUIVALENTS IN MILLIMETERS AND ARE FOR INFORMATION ONLY.



ELECTRICAL CHARACTERISTICS

CHARACTERISTIC IMPEDANCE	77 ± 5 ohms, Method C at 1 MHz
CAPACTIANCE - MUTUAL	30 pF/ft (98 pF/m) (maximum)
ATTENUATION	1.4 dB/100 ft. (4.6 dB/100 m) (maximum) at 1 MHz
SURFACE TRANSFER IMPEDANCE (PER MIL-C-85485 at 30 MHz)	10 milliohms/meter (maximum)

ADDITIONAL REQUIREMENTS

<u>COMPONENT WIRE PRIOR TO CABLING (Per MIL-W-22759)</u>	
ACCELERATED AGING (per MIL-W-22759 Life Cycle Procedure)	300 ± 3°C for 7 hours, .500 in. (12.7 mm) mandrel, .375 lb (170 g), 2.5 kV dielectric test
COLD BEND	-65 ± 2°C for 4 hours, .750 in. (19.1 mm) mandrel, 1.00 lb (454 g)
SHRINKAGE	2.5 kV dielectric test 200 ± 3°C for 6 hours, .125 in. (3.2 mm) (max) in 12 in. (300 mm)
INSULATION RESISTANCE	5000 MΩ for 1000 ft. (1525 MΩ-km) (min)
INSULATION (DIELECTRICS)	
TENSILE STRENGTH	5000 psi (34 N/mm ²) (min)
ELONGATION	50% (min)
IMPULSE DIELECTRIC	8.0 kV (peak), 100% test
<u>FINISHED CABLE (Per MIL-C-27500)</u>	
BLOCKING	200°C for 6 hours
COLD BEND	-65 ± 2°C for 4 hours 6 in. (152 mm) mandrel
CROSSLINKED VERIFICATION	300 ± 5°C for 6 hours 1.75 in. (44.5 mm) mandrel
FLAMMABILITY (Per Raychem Spec 55A, procedure 1)	3 seconds (max); 3 in. (76 mm) (max); no flaming of facial tissue
WEIGHT	21.6 lbs/1000 ft (32.2 kg/km) (nom)
SHIELD COVERAGE	90% (minimum) (each)
JACKET FLAWS	1000 volts, 60 Hz, 100% test
VOLTAGE WITHSTAND (DIELECTRIC)	1000 volts (rms) (min)
JACKET	
WALL THICKNESS	.008 in. (.2 mm) (nominal)
TENSILE STRENGTH	5000 psi (34 N/mm ²) (min)
ELONGATION	50% (min)

The length of lay shall be .75 in. (minimum) to 1.25 in. (maximum).

(+) Designate outer jacket color with a dash number in accordance with MIL-STD-681.

Raychem

Raychem Corporation
300 Constitution Drive
Menlo Park, California 94025
415) 361 3333 TWX 910 373 1205

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCE DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.