

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China







## SPECIFICATION CONTROL DRAWING

7724S3664

**CHEMINAX** 

.0250

.048

.032

.113

.130

.146

77 OHM, AWG 24, 19 STRANDS OF AWG 36, DATA BUS, MIL-STD-1553 OPTIMIZED DOUBLE SHIELD, OUTER SPACE USE

9-3-08 Date D Revision

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

## CONSTRUCTION DETAILS

ELECTRICAL CHARACTERISTICS CHARACTERISTIC IMPEDANCE 77 ± 5 Ohms, Method C at 1 MHz

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED

MUTUAL CAPACITANCE 30.0 pF/ft. (maximum)

**CONDUCTORS** 

**ATTENUATION** 1.4 dB/100 ft. (maximum) at 1 MHz

AWG 24, 19 Strands of AWG 36, Silver-Coated High Strength Copper Alloy

SURFACE TRANSFER IMPEDANCE 10 milliohms/meter (maximum)

**DIELECTRICS** 

(Per MIL-C-85485 at 30 MHz)

Radiation-Crosslinked, Modified ETFE Color - Light Blue/White ADDITIONAL REQUIREMENTS

COMPONENT WIRE PRIOR TO CABLING (Test Procedures per SAE AS22759)

**FILLERS** 

1st SHIELD

AWG 38

Optimized

2<sup>nd</sup> SHIELD

AWG 38

Optimized

**JACKET** 

Silver-Coated Copper

Silver-Coated Copper

Radiation-Crosslinked,

Modified ETFE

CROSSLINK PROOF 300 ± 3°C for 1 hour, .625 inch mandrel,

Radiation-Crosslinked, Modified ETFE INSULATION (DIELECTRIC) .375 lb., 2.5 kV dielectric test

**ELONGATION** TENSILE STRENGTH 50% (minimum) 5000 lbf/in2 (minimum)

**INSULATION FLAWS** SPARK TEST IMPULSE TEST

3.0 kV (rms) 8.0 kV (peak)

INSULATION RESISTANCE LOW TEMPERATURE-COLD BEND

5000 megohms for 1000 ft. (minimum) -65 ± 3°C for 4 hours, .500 inch mandrel,

1.00 lb., 2.5 kV dielectric test

200 ± 3°C for 1 hour, .125 inch (maximum) in 12 inches

**SHRINKAGE** 

**FINISHED CABLE** 

(Test Procedures per NEMA WC 27500, unless otherwise specified)

**BLOCKING** CABLE LAY LENGTH

**CROSSLINKED VERIFICATION** 

**FLAMMABILITY** (Method B of Spec 1200)

**JACKET ELONGATION** 

TENSILE STRENGTH

JACKET FLAWS

SPARK TEST **IMPULSE TEST JACKET THICKNESS** 

LOW TEMPERATURE-COLD BEND

**VOLTAGE WITHSTAND** 

(DIELECTRIC)

200°C for 6 hours

.75 inch (minimum), 1.25 inches (maximum) 300 ± 5°C for 6 hours, 6.00 inch mandrel 3 seconds (maximum); 3 inch (maximum);

no flaming of facial tissue

50% (minimum) 5000 lbf/in2 (minimum)

1.0 kV (rms) 6.0 kV (peak)

.008 inch (nominal) -55 ± 5°C for 4 hours. 6.00 inch mandrel

1500 volts (rms)

WEIGHT 22.0 lbs/1000 ft. (nominal)

Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 7724S3664-9) unless otherwise

specified.

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

**OUTER SPACE REQUIREMENTS** 

RADIATION RESISTANCE 500 megarads/4.25 inch mandrel 1.0 kV dielectric test

**VACUUM STABILITY** 

TOTAL MASS LOSS (TML) **VOLATILE CONDENSABLE** MATERIAL (VCM)

1.00% (maximum) 0.10% (maximum)

WEIGHT LOSS: (Test per Spec 55/)

0.45% (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

The TE logo, Tyco Electronics, Cheminax and Raychem are trademarks.

