



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



SPECIFICATION CONTROL DRAWING

44A0712

TITLE WIRE, ELECTRIC, RADIATION-CROSSLINKED, POLYALKENE INSULATED, SILVER-COATED COPPER, NORMAL WEIGHT, AIRFRAME, 600 VOLT

Date 10-15-93

Revision C

This specification sheet forms a part of the latest issue of Raychem Specification 44 and MIL-W-81044 as applicable.




TABLE I. CONSTRUCTION DETAILS

PART NUMBER	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (in.)		FINISHED WIRE		
			MINIMUM	MAXIMUM	MAXIMUM RESISTANCE AT 20°C (ohms/1000ft)	DIAMETER (in.)	MAXIMUM WEIGHT (lb/1000 ft)
44A0712-24-*	24	19 x 36	.023	.025	24.3	.057 ± .002	3.0
44A0712-22-*	22	19 x 34	.029	.032	15.1	.069 ± .003	4.3
44A0712-20-*	20	19 x 32	.037	.040	9.19	.078 ± .003	6.1
44A0712-18-*	18	19 x 30	.046	.050	5.79	.088 ± .003	8.7
44A0712-16-*	16	19 x 29	.052	.057	4.52	.097 ± .004	10.9
44A0712-14-*	14	19 x 27	.065	.072	2.88	.115 ± .004	16.2
44A0712-12-*	12	37 x 28	.084	.089	1.90	.131 ± .004	24.2
44A0712-10-*	10	37 x 26	.106	.112	1.19	.161 ± .005	36.5
44A0712-8-*	8	133 x 29	.158	.169	.658	.219 ± .006	65.0
44A0712-6-*	6	133 x 27	.198	.213	.418	.269 ± .007	103.
44A0712-4-*	4	133 x 25	.250	.268	.264	.325 ± .008	158.
44A0712-2-*	2	665 x 30	.320	.340	.170	.404 ± .012	252.
44A0712-0-*	0	1045 x 30	.405	.425	.108	.494 ± .016	380.

TABLE II. PERFORMANCE DETAILS

PART NUMBER	BEND TESTING				
	MANDREL DIAMETER (inch) (± 3%)			WEIGHT (lb) (± 3%)	
	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND	WRAP	IMMERSION, LIFE CYCLE AND ACCELERATED AGING	COLD BEND
44A0712-24-*	500	1.00	.250	1.00	3.00
44A0712-22-*	750	1.00	.250	3.00	3.00
44A0712-20-*	750	1.00	.250	4.00	4.00
44A0712-18-*	1.00	1.50	.375	4.00	4.00
44A0712-16-*	1.00	1.50	.375	5.00	5.00
44A0712-14-*	1.50	2.00	.500	5.00	5.00
44A0712-12-*	2.00	2.00	.500	5.00	5.00
44A0712-10-*	3.00	3.00	.750	5.00	5.00
44A0712-8-*	3.00	4.00	.750	6.00	6.00
44A0712-6-*	4.00	5.00	1.00	6.00	10.0
44A0712-4-*	5.00	6.00	1.25	6.00	10.0
44A0712-2-*	6.00	8.00	3.00	6.00	15.0
44A0712-0-*	8.00	10.0	4.00	7.00	15.0

COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-881.

DIMENSIONS ARE IN INCHES, AND UNLESS OTHERWISE DESIGNATED ARE NOMINAL.

Raychem

Raychem Corporation
 300 Constitution Drive, Menlo Park, California 94025
 1-800-2 Raychem FAX: 1-415-361-6297

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms)

ACCELERATED AGING: 300 ± 2°C for 6 hours

Identification legibility, 225 ± 2°C for 6 hours

BLOCKING: 150 ± 2°C for 24 hours

COLOR: White preferred

FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum);
no flaming of facial tissue

HUMIDITY RESISTANCE: Insulation Resistance,
5000 Megohms for 1000 ft. (minimum)

IDENTIFICATION, STRIPING, OR BAND DURABILITY: 125 cycles (250 strokes)
(minimum), 500 g weight

IMMERSION: Diameter increase 5% (maximum); no cracking, no dielectric breakdown

INSULATION ELONGATION AND TENSILE STRENGTH:

Primary Insulation,

Tensile Strength, 2500 lbf/in² (minimum), AWG 24-12

2000 lbf/in² (minimum), AWG 10-0

Elongation, 150% (minimum)

INSULATION FLAWS:

Primary Insulation,

Spark Test, 3.0 kV (rms), 60 Hz, 100% test

Impulse Dielectric Test, 6.0 kV (peak), 100% test

Finished Wire;

Impulse Dielectric Test, 8.0 kV (peak), 100% test

INSULATION RESISTANCE: 5000 megohms for 1000 ft. (minimum)

LIFE CYCLE: 200 ± 2°C for 168 hours

LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours

SHRINKAGE: 300 ± 2°C, 0.125 in. (maximum) in 12 in. AWG 24-12

300 ± 2°C, 0.250 in. (maximum) in 12 in. AWG 10-0

SMOKE: 200 ± 2°C, no visible smoke

SURFACE RESISTANCE: 500 megohms-in. (minimum), both readings

THERMAL SHOCK: 150 ± 2°C, 0.060 in. (maximum)

VOLTAGE WITHSTAND TEST: (POST ENVIRONMENTAL) 2500 volts (rms), 60 Hz, 5 minutes

WICKING: 2.25 in. (maximum)

PART NUMBER: The "" in the part numbers on page one shall be replaced by
color code designators.

Example: AWG 20, white: 44A0712-20-9

AWG 20, white with black stripe: 44A0712-20-90