



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



Description

The 860 *Silicone Heat Transfer Compound* is a low thermal resistance grease with a silicone base that is electrically insulating and non-corrosive. It is used to improve the thermal interface contact conductivity between heat sinks, LEDs, motors, and heat-generating electronic components such as CPUs, GPUs, and power components. It improves the thermal interface between irregular and pitted surfaces.

Benefits & Features

- **High thermal conductivity**
- **Lowers the contact resistance between irregular surfaces.**
- **Extends the life of electronic components**
- **High dielectric strength**
- **Safe on plastics**

Usage Parameters

<i>Properties</i>	<i>Value</i>
Shelf Life	5 y
Theoretical Coverage for 4G Pouch ^{a)}	<656 cm ² <0.70 ft ²

a) Idealized estimate based on 25 µm [1 mil] thickness and 100% transfer efficiency.

Temperature Ranges

<i>Properties</i>	<i>Value</i>
Constant Service Temperature	-40 to 200 °C [-40 to 392 °F]
Storage Temperature Limits	-10 to 40 °C [14 to 104 °F]

Principal Components

Name

Zinc oxide (thermally conductive filler)
Amorphous silica (filler)

CAS Number

1314-13-2
112945-52-5

Properties

<i>Thermal Properties</i>	<i>Method</i>	<i>Value</i>
Thermal Conductivity @25 °C [77 °F] Contact Thermal Resistance @25 °C [77 °F] ^{a)}	Hot Wire Method ASTM E 1225	0.66 W/(m·K) 0.57 x 10 ⁻³ (m ² ·K)/W
<i>Electrical Properties</i>	<i>Method</i>	<i>Value</i>
Volume Resistivity (ρ_v) Volume Conductivity (σ_v) Dielectric Strength @0.254 mm [0.01 mil] Dielectric Constant Dissipation Factor	ASTM D 149 ASTM D 150 "	1.5 x 10 ¹⁵ Ω/cm 6.7 x 10 ⁻¹⁶ S/cm 400 V/mil [16 kV/mm] 3.81 0.0032
<i>Grease Properties</i>	<i>Method</i>	<i>Value</i>
Evaporation Loss, 22 h @165 °C [329 °F] Oil Separation, 30 h @165 °C [329 °F] Dropping Point Water Washout @38 °C [100 °F] ^{b)} Worked Penetration, 60 strokes	ASTM D 2595 ASTM D 6184 ASTM D 566 ASTM D 1264 ASTM D 1403	0.1% 0.7% >260°C [>500 °F] 0.1% 303
<i>Physical Properties</i>	<i>Method</i>	<i>Value</i>
Color Odor Density @25 °C [77 °F] Viscosity Lubricant Bleed @200 °C, 24 h Corrosion Resistant Filler VOC (Volatile Organic Compound) ^{c)}	ASTM D 1475 Estimated	White Odorless 2.40 g/mL Thixotropic paste No ≤2% by weight Yes Zinc oxide, Silica 27%

a) Tested with stainless steel plates

b) Bearing dried at 77 °C [171 °F]

c) According to WHIMS regulation

Storage

Store between -10 and 40 °C [14 and 104 °F] in dry area.

Health, Safety, and Environmental Awareness


Please see the 860 **Safety Data Sheet** (SDS) for greater details on transportation, storage, handling and other security guidelines.

Health and Safety: This product presents low physical and health hazards. Follow good hygiene practices.

HMIS® RATING

HEALTH:	1
FLAMMABILITY:	1
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Environmental Impact: The zinc oxide is classified as a marine pollutant by IMDG criteria. All standard sizes provided can ship as limited quantity products. The 4 g pouch sizes can ship as exempted quantity for dangerous good.

Application Instructions

The conductive grease performance depends on mainly on surface preparation. Improperly prepared contact surfaces can degrade the paste's stability, conductivity, and lubrication characteristics. While the thickness and coverage are also important, the application method itself can easily be adjusted according to performance and application needs.

Prerequisites

- Wear gloves and protective clothing.
- Clean and dry the surface of the substrate to remove other oils and greases, as well as dust, water, solvents, or any other contaminants.
- *Recommendations:* Use MG 824 Isopropyl Alcohol or MG 4351 Thinner

Equipment

- Lint free cloth (for cleaning contact and for wiping excess residue)
- Spatula or stick application tools (sized appropriately for your application)
- Isopropyl alcohol or other residue-free organic solvents

To apply the grease

1. Wipe the contact with a lint-free cloth.
2. Clean the contacts with isopropyl alcohol or other non-oil based cleaner.
3. Once dry, spread grease in a thin layer onto the surface.

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Packaging</i>	<i>Net Volume</i>		<i>Net Weight</i>		<i>Packaging Weights</i>	
860-4G	Pouch	1.7 mL	0.06 fl oz	4 g	0.14 oz	0.56 kg ^{a)}	1.2 lb
860-60G	Jar	25 mL	0.84 fl oz	60 g	2.11 oz	0.59 kg ^{b)}	1.3 lb
860-150G	Tube	62.5 mL	2.11 fl oz	150 g	5.29 oz	0.18 kg	0.40 lb
860-1P	Jar	470 mL	15.9 fl oz	1.13 kg	2.49 lb	1.06 kg	2.34 lb

Contact MG Chemicals if custom packaging or sizes are required

a) Case pack of 100 pouches

b) Case pack of 5

Supporting Products

- *Super Wash Liquid*: Cat. No. 4050-1L, and so on
- *Super Wash Electronic Cleaner*: Cat. No. 406B-425G
- *Thinner*: Cat. No. 4351-1L
- *Isopropyl Alcohol (anhydrous, high purity)*: Cat. No. 824-W or 824-100ML

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.