



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



Description

The 8616 *Super Thermal Grease II* is a low thermal resistance grease with a synthetic oil base that is electrically insulating and non-corrosive. It is used to improve the thermal interface contact conductivity between heat sinks, LEDs, motors, and heat-generating electronic components such as CPUs, GPU chipsets, and power components. It improves the thermal interface between irregular and pitted surfaces.

Benefits & Features

- **High thermal conductivity**
- **Silicone free and non-bleeding**
- **Excellent corrosion resistance**—Passed ASTM B 117 1 000 hours
- **Lowers the contact resistance between irregular surfaces**
- **Extends the life of electronic components**
- **Electrically insulating**
- **Safe on plastics**

Usage Parameters

<i>Properties</i>	<i>Value</i>
Shelf Life	5 y
Theoretical Coverage for 3 mL syringe ^{a)}	<1 180 cm ² <0.64 ft ²

a) Idealized estimate based on 25 μm [1.0 mil] thickness and 100% transfer efficiency.

Temperature Ranges

<i>Properties</i>	<i>Value</i>
Constant Service Temperature	-68 to 165 °C [-90 to 329 °F]
Storage Temperature Limits	-10 to 40 °C [14 to 104 °F]

Principal Components

Name	CAS Number
Aluminum oxide	1344-28-1
Zinc oxide (thermally conductive filler)	1314-13-2

Properties

<i>Thermal Properties</i>	<i>Method</i>	<i>Value</i>
Thermal Conductivity @25 °C [77 °F]	ASTM E 1461	1.78 W/(m·K)
Contact Thermal Resistance ^{a)}	ASTM E 1225	0.24 x 10 ⁻³ (m ² K)/W

a) Tested with stainless steel plates

Electrical Properties	Method	Value
Volume Resistivity (ρ_v)	ASTM D 257	$1.8 \times 10^{11} \Omega \cdot \text{cm}$
Volume Conductivity (σ_v)	"	$5.6 \times 10^{-12} \text{ S/cm}$
Dielectric Strength @50 mil gap	ASTM D 149	330 V/mil [13 kV/mm]
Breakdown Voltage	"	16 600 V [16.6 kV]
Dielectric Constant @1 000 cps	ASTM D 150	6.77
@10 000 cps	"	6.69
Dissipation Factor @1 000 cps	"	0.01
@10 000 cps	"	0.01

TBD=To be determined

Grease Properties	Method	Value
Evaporation Loss, 22 h @165 °C [329 °F]	ASTM D 2595	1.2%
Oil Separation, 30 h @165 °C [329 °F]	ASTM D 6184	0.02%
Dropping Point	ASTM D 2265	>300 °C [>572 °F]
Water Washout @38 °C [100 °F]	ASTM D 1264	0.9%
Worked Penetration, unworked	ASTM D 217	284
60 strokes	"	287
10 000 Strokes	"	313
Salt Spray Corrosion Resistance ^{a)}	ASTM B 117	Pass

Physical Properties	Method	Value
Color		White, silvery
Odor		Odorless
Density @25 °C [77 °F]	ASTM D 1475	2.69 g/mL
Viscosity		Thixotropic paste
Lubricant		No
Bleed		Yes
Corrosion Resistant		Yes
Filler		Aluminum oxide, zinc oxide
VOC (Volatile Organic Compound) ^{b)}	Estimated	17.5%

a) Aluminum 2024 coupons with 254 μm [10 mil] film thickness and 1 000 hours exposure to 5% salt spray

b) According to WHIMS regulation

Synthetic Oil Properties	Method	Value
Oil Viscosity Index ^{c)}	ASTM D 2270	>110
Fire Point ^{d)}	ASTM D 92	321 °C [609.8 °F]
Flash Point	ASTM D 92	>290 °C [>554 °F]

Note: Values based on synthetic oil component only.

c) High oil viscosity index of more than a 100 indicate small oil viscosity change with temperature.

d) Temperature at which oil will continue to burn for at least 5 s after ignition with an open flame.

Storage

Store between -10 and 40 °C [14 and 104 °F] in dry area.

Health, Safety, and Environmental Awareness

Please see the 8616 **Safety Data Sheet** (SDS) for greater details on transportation, storage, handling and other security guidelines.


Environmental Impact: The VOC (volatile organic compound) content is 18% by WHMIS and European standards. Not regulated as a dangerous good for transport.

Health and Safety: Wear safety glasses and disposable gloves to avoid exposures.

HMIS® RATING

HEALTH:	1
FLAMMABILITY:	1
PHYSICAL HAZARD:	0
PERSONAL PROTECTION:	

NFPA® 704 CODES



Approximate HMIS and NFPA Risk Ratings Legend:

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

Application Instructions

The conductive grease performance depends on mainly on surface preparation. Improperly prepared contact surfaces can degrade the paste's stability, conductivity, and lubrication characteristics. While the thickness and coverage are also important, the application method itself can easily be adjusted according to performance and application needs.

Prerequisites

- Wear gloves and protective clothing.
- Clean and dry the surface of the substrate to remove other oils and greases, as well as dust, water, solvents, or any other contaminants.
- *Recommendations:* Use MG 824 Isopropyl Alcohol or MG 4351 Thinner

Equipment

- Lint free cloth (for cleaning contact and for wiping excess residue)
- Spatula or stick application tools (sized appropriately for your application)
- Isopropyl alcohol or other residue-free organic solvents

To apply the grease

1. Wipe the contact with a lint-free cloth.
2. Clean the contacts with isopropyl alcohol or other non-oil based cleaner.
3. Once dry, spread grease in a thin layer onto the surface.



ISO 9001 Registered Quality System.
Burlington, Ontario, Canada QMI File # 004008

Super Thermal Grease II 8616 Technical Data Sheet

8616

Packaging and Supporting Products

<i>Cat. No.</i>	<i>Packaging</i>	<i>Net Volume</i>		<i>Net Weight</i>		<i>Packaging Weights</i>	
8616-3ML	Syringe	3 mL	0.1 fl oz	8.07 g	0.28 oz	0.02 kg	0.04 lb
8616-25ML	Jar	25 mL	0.84 fl oz	67.2 g	2.37 oz	0.63 kg ^{a)}	1.4 lb ^{a)}
8616-85ML	Tube	86 mL	2.93 fl oz	228 g	8.21 oz	TBD	TBD
8616-1P	Jar	483 mL	1.0 pint	1.3 kg	2.86 lb	1.34 kg	2.95 lb
8616-1G	Pail	3.78 L	1.0 gal	10.1 kg	22.4 lb	10.6 kg	23.3 lb

Contact MG Chemicals if custom packaging or sizes are required

TBD=To be determined

a) Case pack of five

Supporting Products

- *Thinner*: Cat. No. 4351-1L
- *Isopropyl Alcohol*: Cat. No. 824-1L

Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at www.mgchemicals.com.

Email: support@mgchemicals.com

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address: **Manufacturing & Support**
1210 Corporate Drive
Burlington, Ontario, Canada
L7L 5R6

Head Office
9347-193rd Street
Surrey, British Columbia, Canada
V4N 4E7

Warranty

M.G. Chemicals Ltd. warranties this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.