

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China









EFD Cores (8995121221)



Part Number: 8995121221

95 EFD CORE SET

EFD (Economical Flat Design) cores have been designed to maximize volume in a low profile geometry. EFD cores allow maximum throughput power density with reasonably low mass for board level installation.

 \Box EFD cores can be supplied with the center post gapped to a mechanical dimension or an A_{τ} value.

Weight indicated is per pair or set.

Weight: 1.8 (g)

Dim	mm	mm tol	nominal inch	inch misc.		
A	12.5	± 0.35	0.492			
В	6.2	± 0.15	0.244	_	Chart Legend ΣΙ/ A : Core Constant, l _e : Effective Path Length, A _e : Effective Cross- Sectional Area, V _e Effective Core Volume	
C	3.5	± 0.20	0.138			
D	4.55	± 0.15	0.179	_		
Е	9	± 0.35	0.354	_		J
F	5.4	± 0.20	0.213			e e
K	2	± 0.10	0.079	_		
					A _L : Inductance Factor	
Expla	ınation	of Part Nur	nbers: Digits 1 & 2	= product class a	and 3 & $4 =$ material grade.	

Electrical Properties				
L v	$850 \pm 25\%$			
Ae(cm ²)	0.11			
$\Sigma l/A(cm^{-1})$	25.9			
$l_e(cm)$	2.84			
$V_e(cm^3)$	0.311			
$A_{min}(cm^2)$	0.108			

 A_L value is measured at 1 kHz, $B \le 10$ gauss.

Fair- Rite Products Corp. • One Commercial Row, Wallkill, New York 12589-0288

888-324-7748 • 845-895-2055 • Fax: 845-895-2629 • ferrites@fair- rite.com • www.fair- rite.com