

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China











SPECIFICATION (Reference sheet)

• Supplier : Samsung electro-mechanics • Samsung P/N: CL05B105KQ5NQNC

• Product : Multi-layer Ceramic Capacitor • Description : CAP, 1µF, 6.3V, ±10%, X7R, 0402

A. Samsung Part Number

<u>CL</u> <u>05</u> <u>B</u> <u>105</u> <u>K</u> <u>Q</u> <u>5</u> <u>N</u> <u>Q</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor			
2	Size	0402 (inch code)	L: 1.0 ± 0.1 mm W: 0.5 ± 0.1 mm		
3	Dielectric	X7R	Inner electrode Ni		
4	Capacitance	1 µF	Termination Cu		
(5)	Capacitance	±10 %	Plating Sn 100% (Pb Free)		
	tolerance		Product Size Control Code		
6	Rated Voltage	6.3 V	Special Reserved for future use		
7	Thickness	0.5 ± 0.1 mm	① Packaging Cardboard Type, 7" reel		

B. Samsung Reliability Test and Judgement condition

	Judgement	Test condition			
Capacitance	Within specified tolerance	1kHz±10% 1.0±0.2Vrms			
Tan δ (DF)	0.1 max.				
Insulation	More than 100Mohm⋅ <i>μ</i> F	Rated Voltage 60~120 sec.			
Resistance					
Appearance	No abnormal exterior appearance	Visual inspection			
Withstanding	No dielectric breakdown or	250% of the rated voltage			
Voltage	mechanical breakdown				
Temperature	X7R				
Characteristics	(From -55℃ to 125℃, Capacitance change should be within ±15%)				
Adhesive Strength	No peeling shall be occur on the	500g·F, for 10±1 sec.			
of Termination	terminal electrode				
Bending Strength	Capacitance change: within ±12.5%	Bending to the limit (1mm)			
		with 1.0mm/sec.			
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder			
	is to be soldered newly	245±5℃, 3±0.3sec.			
		(preheating : 80~120 ℃ for 10~30sec.)			
Resistance to	Capacitance change : within ±7.5%	Solder pot : 270±5 °C, 10±1sec.			
Soldering heat	Tan δ, IR : initial spec.				

	Judgement	Test condition
Vibration Test	Capacitance change : within ±5%	Amplitude : 1.5mm
	Tan δ, IR : initial spec.	From 10Hz to 55Hz (return : 1min.)
		2hours × 3 direction (x, y, z)
Moisture	Capacitance change: within ±12.5%	With rated voltage
Resistance	Tan δ : 0.125 max	40±2℃, 90~95%RH, 500+12/-0hrs
	IR : More than 12.5MΩ·μF	
High Temperature	Capacitance change: within ±12.5%	With 150% of the rated voltage
Resistance	Tan δ : 0.125 max	Max. operating temperature
	IR ∶ More than 25MΩ· μF	
		1000+48/-0hrs
Temperature	Capacitance change: within ±7.5%	1 cycle condition
Cycling	Tan δ, IR : initial spec.	Min. operating temperature → 25 °C
		→ Max. operating temperature → 25°C
		5 cycle test

C. Recommended Soldering method:

Reflow (Reflow Peak Temperature : 260+0/-5°C, 10sec. Max)



A Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.