



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



CHEMTRONICS

Technical Data Sheet

TDS # CTSR

Konform[®] SR

PRODUCT DESCRIPTION

Konform[®] SR provides maximum flexibility for extreme temperatures. This transparent coating provides ideal protection for both rigid and flexible printed circuit boards. Cured coatings are hydrolytically stable and retain their physical electrical properties after high temperature and humidity exposure. Konform[®] SR will not stress delicate circuit components. Konform[®] SR resin meets MIL-I-46058C, Type SR.

- Extends component life by protecting against adverse environments
- Good insulation properties, excellent flexibility
- Resists moisture, salt, fungus, corrosive vapors, and severe environments
- Engineered to withstand heat generated by electronic circuitry as well as climatic temperatures
- Contains a UV indicator for Quality Control inspection using medium intensity light at 265-335 nm
- UL Recognized, File E76307
- Compliant to IPC-CC-830A
- RoHS compliant

TYPICAL APPLICATIONS

Konform[®] SR is ideal for applications in:

- Aerospace
- Data Communications
- Instrumentation
- Automotive Manufacturing
- Marine Manufacturing
- Process Control

TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

Usable Temp. Range of Cured Coatings	(-85°F to 390°F) (-65°C to 200°C)
Tack Free Time	15 min.
Curing Conditions: Full Cure (@ 80% R.H.)	24 Hours @ 77°F (25°C) or 8 Hours @ 170° (77°C)
Quick Cure	10 min. @RT followed by 10 min @ 80°C
Specific Gravity (Water=1) @ 68°F	0.74 (Liquid only)
Viscosity (cps @ 77°F)	40 ± 5 cps
Flash Point (TCC)	60°F
Volume Resistivity (ohm/cm)	1.5 x 10 ¹⁶
Dielectric Breakdown (volts/mil)	1100
Thermal Conductivity (Cal-cm/sec-cm ² -°C)	2.9 x 10 ⁻⁴
Coefficient of Thermal Expansion (in/in/°C)	2.1 x 10 ⁻⁴
Coverage (1 mil/ft ²)	CTSR-1 250.9 CTSR-12 21.0
Shelflife	1 year from manufacture
Comparative Tracking Index (CTI)	225 V; PLC3

COMPATIBILITY

Konform[®] SR is generally compatible with most materials found on printed circuit boards. As with any chemical product, product/component compatibility must be determined on a non-critical area prior to use.

Performance

Moisture Resistance	Excellent
Removability	Excellent
Ease of Repair	Excellent
Flexibility	Excellent
Adhesion	Excellent
Abrasion Resistance	Fair
Solvent Resistance	Good

USAGE INSTRUCTIONS

For industrial use only.

Read MSDS carefully prior to use.

Before applying Konform[®] SR conformal coatings, clean circuit boards to remove contamination and allow to dry. Cleaning may be performed with Chemtronics Flux-Off[®] products.

SPRAY APPLICATION: Apply top to bottom, allowing coating to flow evenly around components. Rotate PCB 90° and repeat application. Rotate and apply coating two additional times, then allow board to cure. If additional thickness is desired, apply additional coatings. When using liquid spray with automatic dispensing equipment, adjustments may be required in application rate and viscosity.

DIP APPLICATION: Using automatic equipment or hand immersion technique, slowly immerse PCB into the coating and remove slowly. Use an average rate of approximately 1 foot per minute. After allowing the board to cure, process may be repeated to achieve desired thickness.

BRUSH APPLICATIONS: Evenly apply coating to areas desired at thickness required. Allow time for curing before reapplying to achieve a thick coating. Use Chemask[®] to protect components during conformal coating process. After application, cured Konform[®] SR may be removed by soaking in Chemtronics Electro-Wash[®] Two Step.

AVAILABILITY

CTSR-12	10 oz. Aerosol
CTSR1	1 Gallon Liquid
CTSR5	5 Gallon Liquid

ENVIRONMENTAL IMPACT DATA

(For Aerosol Product)

ENVIRONMENTAL IMPACT DATA

CFC	0.0%	VOC	88.0%
HCFC	0.0%	HFC	0.0%
Cl. Solv.	0.0%	ODP	0.00

CFC, HCFC, CL. SOLV., VOC, and HFC numbers shown are the content by weight. Ozone depletion potential (ODP) is determined in accordance with the Montreal Protocol and U.S. Clean Air Act of 1990. The ODP of this product is 0.0. It is the sum of the ODP of the substances that may contribute to the depletion of stratospheric ozone, based upon the weight of each substance in the product's formulation.

TECHNICAL & APPLICATION ASSISTANCE

Chemtronics provides a technical hotline to answer your technical and application related questions. The toll free number is: **1-800-TECH-401**.

NOTE: This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

CHEMTRONICS

8125 COBB CENTER DRIVE
KENNESAW, GA 30152

1-770-424-4888

REV. K (08/13)

Chemtronics[®], Electro-Wash[®], Flux-Off[®], Chemask[®], and Konform[®] are registered trademarks of Chemtronics. All rights reserved.

DISTRIBUTED BY: