



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China



# CHEMTRONICS

## Technical Data Sheet

**TDS # CW8**

### Chemask<sup>®</sup> W

#### PRODUCT DESCRIPTION

Chemask<sup>®</sup> W solder mask is water soluble and designed to be removed with most aqueous cleaning systems. Chemask<sup>®</sup> W contains high temperature compounds that protect component-free areas from solder during wave soldering. This water soluble formulation is stable to rosin, organic and inorganic fluxes.

- Protects boards from molten solder to 515°F (268°C)
- Compatible with most flux types
- Leaves no corrosive residue
- Non-contaminating
- UV Detectable

#### TYPICAL APPLICATIONS

During wave soldering, Chemask<sup>®</sup> W protects:

- Component Free Areas
- Gold Connectors
- Gold Fingers
- Pin Connectors

#### TYPICAL PRODUCT DATA AND PHYSICAL PROPERTIES

<b>Base Material</b>	Synthetic Resin
<b>Color</b>	Blue
<b>Solvent Stability</b>	Dissolves in water with or without detergent
<b>Flux Compatibility</b>	Aqueous Flux
<b>Temperature Stability</b>	515°F (268°C)
<b>Tack-Free Drying Time (10 mils @ 77°F)</b>	20 min.
<b>Cure Time (10 mils @ 77°F)</b>	1 hr.
<b>Viscosity (@ 77°F) (± 300 cps)</b>	15,000 cps
<b>Viscosity Adjusted With</b>	DI Water
<b>Contains UV Indicator</b>	Yes
<b>Solids Content</b>	~ 40%
<b>Flash Point</b>	Nonflammable
<b>Weight/Gallon</b>	8.8 lbs.
<b>Shelflife</b>	1 year

#### COMPATIBILITY

Chemask<sup>®</sup> W is generally compatible with most materials used in printed circuit board fabrication. As with any solder masking agent, compatibility with substrate must be determined on a non-critical area prior to use.

### APPLICATION METHOD

Squeeze Bottle/Syringe	Yes
Spatula	Yes
Screening	Yes
Stencil	Yes
Automatic Dispensing	Yes

### USAGE INSTRUCTIONS

For industrial use only.

Read MSDS carefully prior to use.

Chemask® W solder masking agent is engineered for all electronic manufacturing applications. When applying by hand using squeeze bottle or spatula, insure that all areas of the pre-tinned hole are evenly covered on the side to be soldered. For screening applications, properly clean and prepare screen, then apply masking agent in the same manner as solder paste. Automatic dispensing equipment may also be used as appropriate.

**REMOVAL:** After allowing the mask to become fully cured, the mask may be washed away with water. For optimum performance, water soluble mask may be removed with agitation, ultrasonic, or industrial washing. Surfactants may be added to increase cleaning efficiency.

### AVAILABILITY

CW8 8 oz. Squeeze Bottle

### TECHNICAL & APPLICATION ASSISTANCE

Chemtronics provides a technical hotline to answer your technical and application related questions. The toll free number is: **1-800-TECH-401**.

### ENVIRONMENTAL IMPACT DATA

#### ENVIRONMENTAL IMPACT DATA

CFC	0.0%	VOC	5.0%
HCFC	0.0%	HFC	0.0%
Cl. Solv.	0.0%	ODP	0.00

CFC, HCFC, CL. SOLV., VOC, and HFC numbers shown are the content by weight. Ozone depletion potential (ODP) is determined in accordance with the Montreal Protocol and U.S. Clean Air Act of 1990. The ODP of this product is 0.0. It is the sum of the ODP of the substances that may contribute to the depletion of stratospheric ozone, based upon the weight of each substance in the product's formulation.

### NOTE:

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. CHEMTRONICS does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.

### CHEMTRONICS

8125 COBB CENTER DRIVE

KENNESAW, GA 30152

1-770-424-4888

REV. G (08/13)

### DISTRIBUTED BY: