

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China









RW-2500/1 Revision 4 Page 1 of 6 September 2014

Specification RW-2500/1

TE 108-121004

HIGH TEMPERATURE HEAT SHRINK IDENTIFICATION MARKER SLEEVES - HTMS (HTTMS)

Approved Signatories:

This document is electronically reviewed and approved by TE Connectivity.



RW-2500/1 Revision 4 Page 2 of 6 September 2014

1. REVISION HISTORY

Revision Number	Description of change	Date	Incorporated By
1	AFC 256	14/04/04	Alan Kean
2	AFC 403	13/02/06	John Swift
3	AFC 421	17/07/06	Gordon White and Steve Rowland
4	Refer to PCN	24/09/14	Lee Smith

2. SCOPE

This specification sheet, when used with RW-2500, defines the product characteristics and performance of TE Connectivity High Temperature Heat Shrink Identification Marker Sleeves.

The IBM daisy wheel printer and ink cartridge developed for HTMS is now obsolete. TE can only guarantee the performance properties covered in this standard, and not any marking applied using non-recommended printing systems. Where non-standard systems are used, customers are required to carry out their own validation testing.

This system is not recommended where strain relief properties are required. Product is available in 2:1 shrink ratio.

Unless specified, the tube size for qualification testing is 6.4mm (1/4 inch).

3. REQUIREMENTS

3.1. MATERIAL

The sleeving shall be fabricated from irradiated, thermally stabilized, modified polyvinylidene fluoride compound. It shall be homogeneous and essentially free from flaws, defects, pinholes, bubbles, seams, cracks or inclusions.

3.2. COLOR

The sleeves shall be supplied in white, unless otherwise specified.

3.3. PROPERTIES

The sleeves shall meet the requirements of Table 3.

3.4. FORM

The sleeves shall be cut lengths in accordance with Table 1.



RW-2500/1 Revision 4 Page 3 of 6 September 2014




Figure 1: HTMS System 90 Assembly



RW-2500/1 Revision 4 Page 4 of 6 September 2014

TABLE 1 Dimensions

USA DESCRIPTIONS

	As Supplied			Recovered				
Product Description	Inside Diameter Minimum		Marking Length Minimum		Inside Diameter Maximum		Wall Thickness	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.
HTTMS-3/32-1.50	0.093	2.36	1.50	39.41	0.031	0.79	0.016 + 0.003	0.41+0.08
HTTMS-1/8-1.50	0.125	3.17	1.50	39.41	0.062	1.57	0.013 + 0.003	0.33+0.08
HTTMS-3/16-1.50	0.187	4.74	1.50	39.41	0.093	2.36	0.015 + 0.003	0.38+0.08
HTTMS-1/4-1.50	0.250	6.35	1.50	39.41	0.125	3.17	0.015 + 0.003	0.38+0.08
HTTMS-3/8-1.50	0.375	9.50	1.50	39.41	0.187	4.74	0.015 + 0.003	0.38+0.08
HTTMS-1/2-1.50	0.475	12.07	1.50	39.41	0.250	6.35	0.015 + 0.003	0.38+0.08
HTTMS-3/4-1.50	N/A	N/A	1.50	39.41	0.375	9.53	0.017 + 0.003	0.43+0.08
HTTMS-3/32-1.75	0.093	2.36	1.75	44.45	0.031	0.79	0.016 + 0.003	0.41+0.08
HTTMS-1/8-1.75	0.125	3.17	1.75	44.45	0.062	1.57	0.013 + 0.003	0.33+0.08
HTTMS-3/16-1.75	0.187	4.74	1.75	44.45	0.093	2.36	0.015 + 0.003	0.38+0.08
HTTMS-1/4-1.75	0.250	6.35	1.75	44.45	0.125	3.17	0.015 + 0.003	0.38+0.08
HTTMS-3/8-1.75	0.375	9.50	1.75	44.45	0.187	4.74	0.015 + 0.003	0.38+0.08
HTTMS-3/4-1.75	N/A	N/A	1.75	44.45	0.375	9.53	0.017 + 0.003	0.43+0.08

EUROPEAN DESCRIPTIONS

	As Supplied			Recovered				
Product Description	Inside Diameter Minimum		Marking Length Minimum		Inside Diameter Maximum		Wall Thickness	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.
HTMS-3/32	0.093	2.36	1.89	48	0.031	0.79	0.016 + 0.003	0.41+0.08
HTMS-1/8	0.125	3.17	1.89	48	0.062	1.57	0.013 + 0.003	0.33+0.08
HTMS-3/16	0.187	4.74	1.89	48	0.093	2.36	0.015 + 0.003	0.38+0.08
HTMS-1/4	0.250	6.35	1.89	48	0.125	3.17	0.015 + 0.003	0.38+0.08
HTMS (HTTMS)-3/8	0.375	9.50	1.85	47	0.187	4.74	0.015 + 0.003	0.38+0.08
HTMS (HTTMS)-1/2	0.475	12.07	1.81	46	0.250	6.35	0.015 + 0.003	0.38+0.08
HTMS (HTTMS)-3/4	N/A	N/A	1.65	42	0.375	9.53	0.017 + 0.003	0.43+0.08

TABLE 2
Mandrel Dimensions for Heat Shock, Heat Aging and Low Temperature Flexibility

Tubing Size	Mandrel Diameter		
Tubing Size	in	mm	
3/32 through 3/16	5/16	7.9	
1/4 through 3/4	3/4	19.0	



RW-2500/1 Revision 4 Page 5 of 6 September 2014

TABLE 3 Requirements

TABLE 3 nequirements							
PROPERTY	UNIT	REQUIREMENT	RW-2500 TEST METHOD				
PHYSICAL	mm (inches)	In accordance with Table 1					
Dimensions	min (mones)	III accordance with Table 1	RW-2500 Section				
Dimensional Recovery 3 minutes at 200°C (392°F)	mm (inches)	In accordance with Table 1	4.3.1.1				
Longitudinal Change 3 minutes at 200°C (392°F)	Percent	10 maximum	ASTM D 2671				
Tensile Strength	MPa (psi)	34.5 (5000) minimum	RW-2500 Section 4.3.2.1 ASTM D 2671				
Ultimate Elongation	Percent	200 minimum	2 inches/minute				
Specific Gravity		1.8 maximum	RW-2500 Section 4.3.3 ASTM D 2671				
Low Temperature Flexibility 4 hours at -55°C (-67°F)		No cracking	RW-2500 Section 4.3.5.1				
Heat Shock			RW-2500 Section				
4 hours at 275°C (527°F)		No dripping, flowing, or cracking	4.3.6.1				
Heat Aging			RW-2500 Section				
168 hours at 225°C (437°F)		No cracking	4.3.7.1				
Copper Contact Corrosion			RW-2500 Section				
16 hours at 150° C (302°F)		No pitting or blackening of core	4.3.14.1				
Pull-Off Force							
Size: 3/32 through 1/8	N (Pounds)	22 (5.0) maximum	RW-2500 Section 4.3.8				
Size: 3/16 through 1/4	N (Pounds)	31 (7.0) maximum					
Size: 3/8 through 3/4	N (Pounds)	44 (10.0) maximum					
Vacuum Outgassing			RW-2500 Section				
TML (Total Mass Loss)			4.3.18 ASTM E 595				
VCM (Volatile Condensable	Percent	1.0 maximum					
Material)	Percent	0.1 maximum					
Temperature Cycling							
6 cycles of:			RW-2500 Section				
0.5 hr/-196°C (-321° F)		No cracking	4.3.23				
0.5 hr/200°C (392° F) ELECTRICAL		INO Cracking					
Dielectric Strength			RW-2500 Section				
Size: 3/32 through 3/16		31.5 (800) minimum	4.3.11.1				
1/4 through 1/2	kV/mm (V/mil)	23.6 (600) minimum	ASTM D 2671				
1/ 1 tinough 1/2	(V/111111 (V/111111)	20.5 (000) Hillimidili	RW-2500 Section				
Volume Resistivity	ohm-cm	10 ¹² minimum	4.3.12.1 ASTM D 2671				
CHEMICAL			RW-2500 Section				
Corrosive Effect		Non Corrosive	4.3.13.1				
16 hours at 150°C (302°F)			ASTM D 2671				
Flammability							
UL 224		Pass VW-1	RW-2500 Section				
ASTM D 876 Average time of burning	Seconds	15 maximum	4.3.15.1 and				
			Section 4.3.15.2				
Fungus Resistance		Rating of 1 or less	ASTM G 21				



RW-2500/1 Revision 4 Page 6 of 6 September 2014

Additional notes for Low Temperature Flexibility

For sizes smaller than 1/4 inch, recover three 6-inch long specimens and cool to room temperature.

For sizes 1/4 inch and larger, prepare test strips as follows: Recover three 6-inch long sections of tubing, and while they are still hot, slit longitudinally, and flatten between metal plates. Cool to room temperature, remove metal plates, and cut into 1/4-inch wide strips.

Place the specimens in a cold chamber with the mandrel specified in Table 2 at -55°C (-67°F) for 4 hours. While still in the cold chamber, and at this same temperature, wrap the specimens around the mandrel not less than 360° in approximately 2 seconds.