imall

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





NT-MIL

Flexible, rugged, modified elastomeric heat-shrinkable tubing

NT-MIL modified elastomeric heatshrinkable tubing offers outstanding resistance to abrasion and physical abuse while providing flexibility and strain relief needed in many harnessing applications. NT-MIL tubing is widely used for insulation, strain relief and abrasion protection on cable harnesses and wire bundles in the military and aerospace industries. It meets the stringent requirements of AMS-DTL-23053/1, Classes 1 and 2.

Temperature rating

NT-MIL tubing remains flexible at temperatures as low as -70°C without cracking. It also withstands heat

shock at 200°C without dripping, flowing or cracking.

NT-MIL tubing is resistant to common fluids and solvents including aviation and ground vehicle fuels, lubricating oil, and hydraulic fluids. It retains excellent physical and electrical properties following exposure. No special skills are required to install NT-MIL tubing. Using standard heating tools, one operator can complete an installation in minutes, substantially reducing labor costs.

NT-MIL tubing is supplied in a wide range of sizes. Because NT-MIL is heat-shrinkable, each size can accommodate a variety of harness sizes, minimizing inventory and related costs.

Full recovery temperature:	135°C
Continuous operating temperature:	–70°C to 121°C

Specifications*

Туре	Raychem	Military	
NT-MIL	RW-3030	AMS-DTL-23053/1, Cl. 1 and 2	
*When ordering, alv	vavs specify latest issue.		

Dimensions (millimeters/inches)



	Inside diameter			Wall thickness		Inside diameter				Wall thickness			
	D (min.) Expanded as supplied		d (max.) Recovered after heating		W Recovered after heating**		Size	D (min.) Expanded as supplied		d (max.) Recovered after heating		W Recovered after heating**	
Size													
1/8	3.2	0.125	1.6	0.062	0.66 ± 0.20	0.026 ± 0.008	1	25.4	1.000	14.5	0.570	1.77 ± 0.51	0.070 ± 0.020
3/16	4.8	0.187	2.4	0.093	0.84 ± 0.25	0.033 ± 0.010	1 1/4	31.8	1.250	18.1	0.714	2.20 ± 0.51	0.087 ± 0.020
1/4	6.4	0.250	3.6	0.143	0.89 ± 0.25	0.035 ± 0.010	1 1/2	38.1	1.500	21.8	0.857	2.41 ± 0.51	0.095 ± 0.020
3/8	9.5	0.375	5.4	0.211	1.01 ± 0.25	0.040 ± 0.010	1 3/4	44.5	1.750	25.4	1.000	2.71 ± 0.51	0.107 ± 0.020
1/2	12.7	0.500	7.3	0.286	1.21 ± 0.38	0.048 ± 0.015	2	50.8	2.000	29.0	1.140	2.79 ± 0.51	0.110 ± 0.020
5/8	15.9	0.625	9.1	0.357	1.32 ± 0.38	0.052 ± 0.015	3	76.2	3.000	43.4	1.710	3.17 ± 0.51	0.125 ± 0.020
3/4	19.1	0.750	10.9	0.428	1.44 ± 0.38	0.057 ± 0.015	4	101.6	4.000	57.9	2.280	3.55 ± 0.51	0.140 ± 0.020
7/8	22.2	0.875	12.7	0.500	1.65 ± 0.38	0.065 ± 0.015							

**Wall thickness will be less if tubing recovery is restricted during shrinkage.

Ordering information

Colors	Black
Size selection	Always order the largest size that will shrink snugly over the component being covered.
Standard packaging	On spools
Ordering description	Specify product name, size, and color; for example, NT-MIL 1/4-0 (0=Black).

Specification values

	Property	Unit	Requirement	Method of test	
Material	Dimensions	mm <i>(inches)</i>	See Reverse	ASTM D 2671	
	Longitudinal change	percent	+1, -10	ASTM D 2671	
	Tensile strength	psi <i>(Mpa)</i>	1500 <i>(10.3)</i> minimum	ASTM D 412	
	Ultimate elongation	percent	225 minimum	ASTM D 412	
	Tensile stress at 200% elongation	psi <i>(Mpa)</i>	1500 <i>(10.3)</i> maximum	AMS-DTL-23053	
	Restricted shrinkage (30 minutes at 135°C/ <i>275°F</i>)		No cracks	AMS-DTL-23053	
	Followed by test for:				
	Voltage withstand		Pass		
	Low temperature flexibility (4 hours at -70°C/-94°F)		No cracks	AMS-DTL-23053	
	Heat shock (4 hours at 200°C/ <i>392°F</i>)		No cracks, flowing or dripping	AMS-DTL-23053	
	Heat resistance (168 hours at 121°C/ <i>250°F</i>)			ASTM D 2671	
	Followed by tests for:		1200 <i>(8.3)</i> minimum		
	Tensile strength	psi <i>(Mpa)</i>	ASTM D 412		
	Ultimate elongation	percent	175 minimum	ASTM D 412	
	Dielectric strength	volts/mil <i>(kv/mm)</i>	Sizes up to 7/8: 300 <i>(11.8)</i> minimum Sizes 1 and larger: 200 <i>(7.8)</i> minimum	ASTM D 2671	
Electrical	Dielectric strength	volts/mil <i>(kv/mm)</i>	Sizes up to 7/8: 300 <i>(11.8)</i> minimum Sizes 1 and larger:	ASTM D 2671	
			200 <i>(7.8)</i> minimum		
0	Volume resistivity	ohm-cm	1 x 10 ¹¹ minimum	ASTM D 876	
Chemical	Copper mirror corrosion (16 hours at 150°C/ <i>302°F</i>)		No pitting or corrosion	AMS-DTL-23053	
	Copper contact corrosion (16 hours at 150°C/ <i>302°F</i>)		No pitting or blackening of copper		
	Flammability		Self-extinguishing in 15 seconds; 3 inches maximum burn length	ASTM D 2671 Procedure A	
	Fungus resistance		No growth	ASTM G 21	
	Water absorption (24 hours at 23°C/ <i>73°F</i>)	percent	1.0 maximum	ASTM D 570	
、	Fluid resistance (24 hours at 23°C/ <i>73°F</i>) in: JP-8 fuel (MIL-T-83133) Hydraulic fluid (MIL-H-5606) Lubricating oil (MIL-L-7808) Lubricating oil (MIL-L 23699) Salt water (5% salt) Anti-icing fluid (MIL-A-8243)			AMS-DTL-23053	
	Followed by tests for:				
	Tensile strength	psi <i>(Mpa)</i>	1000 <i>(6.9)</i> minimum	ASTM D 412	
	Ultimate elongation	percent	175 minimum	ASTM D 412	
	Dielectric strength	volts/mil (kV/mm)	250 <i>(9.8)</i> minimum	ASTM D 2671	
	for specific details about test procedures. rk of Tyco Electronics Corporation.				
Tyco Electronics Corp 300 Constitution Drive Menlo Park, CA 94025- USA Tel: (800) 926-2425 (US Tel: +1 (650) 361-3860 (Faraday Road Dorcan, Swindon, St United Kingdom & Canada) Tel: +44 1793 52817	N3 5HH Kawas Japan 1 Tel: +8	aki, Kanagawa 214-8533 1 44 900 5102	Asia Pacific Headquarters 26 Ang Mo Kio, Industrial Park 2 Singapore 569507 Tel: +65 4866 151	

All information, including illustrations, is believed to be reliable. Users, however, should independently evaluate the suitability of each product for their application. Tyco Electronics Corporation makes no waranties as to the accuracy or completeness of the information, and disclaims any liability regarding its use. Tyco Electronics Corporation's only obligations are those in the Standard Terms and Conditions of Sale for these products and in no case will Tyco Electronics Corporation be liable for any incidental, indirect, or consequential damages arising from the sale, resale, use, or misuse of the product. Tyco Electronics Corporation's Specifications are subject to change without notice. In addition, Tyco Electronics Corporation reserves the right to make changes in materials or processing without notification to the Buyer which do not affect compliance with any applicable specification.