imall

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





Economical And Easy **To Install**

- Resists Gasoline, **Engine Chemicals And Cleaning Solvents**
- Expands Up To 150%
- Cut And Abrasion Resistant
- FMVSS 302 Approval



Hot Knife

Material **Polyethylene Terepthalate**

Grade PTN

Monofilament Diameter .010"

Drawing Number TF001PET-WD



www.techflex.com 800.323.5140 • 973.300.9242 • fax: 973.300.9409 104 Demarest Road • Sparta, NJ 07871

Nominal	Part	Expansion Range		Bulk	Shop	Available	Lbs/
Size	#	Min	Max	Spool	Spool	Colors	100'
1/16"	PTN0.06	3/64"	3/32"	1,000'	250'		0.22
1/8″	PTN0.13	3/32″	1/4″	1,000′	225′		0.20
1/4″	PTN0.25	1/8″	7/16″	1,000′	200′		0.30
3/8″	PTN0.38	3/16″	1/2″	500′	125′		0.57
1/2″	PTN0.50	1/4″	3/4″	500′	100′	more	0.77
5/8″	PTN0.63	3/8″	1″	500′	100′	than	0.95
3/4″	PTN0.75	1/2″	1 1/4″	250′	75′	30	1.20
1″	PTN1.00	5/8″	1 5/8″	250′	65′		1.34
1 1/4″	PTN1.25	3/4″	1 3/4″	250′	50′		1.60
1 1/2″	PTN1.50	1″	2 1/8″	200′	40′		1.96
1 3/4″	PTN1.75	1 1/4″	2 3/4″	200′	30′		2.45
2″	PTN2.00	1 1/2″	3 1/2″	200′	50′		2.60
2 1/2″	PTN2.50	1 3/4″	3 5/8″	200′	50′		3.80
3″	PTN3.00	2 1/2″	4 3/4″	100′	50′	BK,CL,NB,RE	4.00
3 END CONSTRUCTION					•		
1/4″	PT30.25	1/8″	3/8″	1,000′	200′	4	0.39
9 MIL CONSTRUCTION							
4″	PT94.00BK	4″	6 1/2″	100′	50′	BK	3.80
PET LEAN							
3/4″	PTL0.75BK	1/2″	1 1/4″	250′	75′	BK	1.04
1 1/4″	PTL1.25BK	3/4″	1 3/4″	250′	50′	BK	1.19


Put-Ups

A Versatile Bundling And Protection Solution

The FLEXO® Original braided from 10 mil polyethylene terepthalate (PET) monofilament yarns. The material has a wide operating temperature range, is resistant to chemical degradation, UV radiation, and abrasion. Used in electronics, automotive, marine and industrial wire harnessing applications where cost efficiency and durability are critical.

The unique braided construction and wide expandability allows quick and easy installation over large connectors and long runs.

High thermal and chemical resistance and wide color/size selection make FLEXO® Original PET ideal for customizing and protecting the wires, hoses and cables in custom and classic colors.







700°

8009

500°

400° 300°

200°

100°

-200°

TEMPERATURES

OPERATING



Abrasion Resistance Medium

Abrasion Test Machine **Taber 5150**

Abrasion Test Wheel **Calibrase H-18**

Abrasion Test Load 500g

Room Temperature 77°F

Humidity 72%

Two Broken Filament 300 Test Cycles

Approximately 6 Broken Filaments 500 Test Cycles

Material Destroyed - Very Visible Hole In Material 1,150 Test Cycles

Pre-Test Weight 4,547.4 mg

Post-Test Weight 4,133.9 mg

Test End Loss Of Mass Point Of Destruction 413.5 mg

UL94VO, FAR25, Rating

FMVSS-302

482°F (250°C)						
Maximum Continuous Mil-I-23053						
257°F (125°C)						

Melt Point

ASTM D-2117

Minimum Continuous -94°F (-70°C)

www.techflex.com

CHEMICAL RESISTANCE

1=No Effect 2=Little Effect 3=Affected

4=More Affected 5=Severely Affected

Aromatic Solvents	2
Aliphatic Solvents	
Chlorinated Solvents	
Weak Bases	
 Salts	
Strong Bases	
Salt Water 0-S-1926	
Hydraulic Fluid <i>MIL-H-5606</i>	1
Lube Oil <i>MIL-L-7808</i>	1
De-lcing Fluid <i>MIL-A-8243</i>	1
Strong Acids	3
Strong Oxidants	2
Esters/Keytones	1
UV Light	1
Petroleum	
Fungus ASTM G-21	
Halogen FreeY	es
RoHSY	es
SVHCNor	ne

PHYSICAL **PROPERTIES**

Monofilament Diameter ASTM D-204	010
Flammability Rating FMVSS-302 Approved	UL94
Recommended Cutting	_Hot Knife
Colors	<30
Wall Thickness	.025
Tensile Strength (Yarn) ASTM D-2256 Lbs	7.5
Specific Gravity ASTM D-792_	1.38
Moisture Absorption % ASTM D-570	.12
Hard Vacuum Data ASTM E-595 at 10-5 torr	
TML	19
CVCM	.00
WVR	16
Smoke D-Max ASTM E-662	56
Outgassing	Med
Oxygen Index ASTM D-2863	21

© 2015 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden.

Techflex product names and logos are registered trademarks of Techflex, Inc., unless otherwise attributed. The contents and illustrations contained herein are believed to be reliable. Techflex makes no warranties as to their accuracy or completeness and disclaims any liability in connection with their use. Techflex's only obligations are those in standard terms of sale for these products and Techflex will not be liable for any consequential or other damages arising due to misuse of these products or typographical errors or omissions. Users should make their own evaluation to determine the suitability of these products for their unique and specific applications. 11-15









- Custom combination colors manufacterd by Techflex
- The possiblites are endless!

