



Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from,Europe,America and south Asia,supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of “Quality Parts,Customers Priority,Honest Operation,and Considerate Service”,our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip,ALPS,ROHM,Xilinx,Pulse,ON,Everlight and Freescale. Main products comprise IC,Modules,Potentiometer,IC Socket,Relay,Connector.Our parts cover such applications as commercial,industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



## Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





# Introducing RMW

Rugged, medium wall RMW tubing is specifically designed for use in a broad range of low-voltage applications. RMW is tough and flexible, making it particularly suited for the insulation and protection of cable joints in low voltage electrical systems as well as for cable repair. Uncoated RMW provides insulation and strain relief. Adhesive-lined RMW also provides an environmental seal. RMW is a good choice for applications where maximum reliability and product performance and simplified installation are required.

## KEY FEATURES

- Withstands mechanical abuse for increased product reliability
- Resistant to impact and abrasion
- Resistant to chemicals and moisture
- Adhesive-lined version provides a complete moisture-proof seal preventing corrosion of underlying components
- Adhesive liner specially formulated to seal to most common insulation materials including crosslinked polyolefin, PVC, neoprene and other elastomeric materials as well as most metals
- Available in sizes ranging from 10mm to 285mm as supplied to cover a wide range of cable sizes and splice diameters
- Fast easy installation with a torch or heat gun
- High shrink ratio to cover uneven substrates
- UV Resistant
- RoHS compliant

## APPLICATIONS

- Power Distribution
- Trucks and buses
- Heavy Equipment
- Rail cars and locomotives
- Shipyards
- Underground wells

**SAMPLES NOW AVAILABLE**

[te.com/products/RMW](http://te.com/products/RMW)

## ELECTRICAL

- Medium wall provides reliable electrical insulation

## MECHANICAL

- Medium wall withstands mechanical abuse
- Resistant to impact and abrasion
- Provides strain relief when installed on splices and joints
- Particularly suited for cable jacket repair

## TEMPERATURE RATING

- Full recovery temperature: 125°C [257°F]
- Operating Temperature range: -40°C to 110°C [-40°F to 230°F]

## STANDARDS AND SPECIFICATIONS


- RMW SCD

## ORDERING INFORMATION

- Color: Black only
- Standard packaging: 1200MM lengths
- Ordering description: Specify product name, size, length, coating and color; for example, RMW-16/5-1200/ADH-0.
- Always order the largest size that will shrink snugly around the component being covered.
- Special cut lengths are available upon request.
- Marking: Tubing will be marked with product name, size and batch number.



**RMW DIMENSIONS**



Size	Minimum Expanded I.D. (D)		Maximum Expanded I.D. (d)		Nominal Recovered Jacket Wall (W minus W1)		Nominal Recovered Adhesive Wall (W1)	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.
10/3	.394	10	.118	3	.039	1.0	.010	.25
16/5	.630	16	.197	5	.055	1.4	.012	.30
25/8	.984	25	.315	8	.079	2.0	.014	.35
35/12	1.378	35	.472	12	.079	2.0	.014	.35
50/16	1.968	50	.630	16	.079	2.0	.014	.35
63/19	2.480	63	.748	19	.095	2.4	.016	.40
75/22	2.953	75	.866	22	.106	2.7	.016	.40
85/25	3.346	85	.984	25	.110	2.8	.016	.40
95/29	3.740	95	1.142	29	.122	3.1	.018	.45
115/34	4.527	115	1.339	34	.122	3.1	.018	.45
140/42	5.512	140	1.654	42	.122	3.1	.018	.45
160/50	6.300	160	1.968	50	.126	3.2	.020	.50
180/60	7.087	180	2.362	60	.126	3.2	.020	.50
245/80*	9.646	245	3.150	80	.095	2.4	N/A	N/A
285/135*	11.220	285	5.315	135	.055	1.4	N/A	N/A

\*Uncoated only

**PRODUCT OFFERING**

Material Description	Material Number
RMW-10/3-1200/ADH-O	C71645-000
RMW-10/3-1200/U-O	F35964-000
RMW-115/34-1200/ADH-O	C12980-000
RMW-115/34-1200/U-O	E34697-000
RMW-140/42-1200/ADH-O	C31677-000
RMW-140/42-1200/U-O	E64798-000
RMW-16/5-1200/ADH-O	397892-000
RMW-16/5-1200/U-O	F43323-000
RMW-160/50-1200/ADH-O	F46631-000
RMW-160/50-1200/U-O	E24686-000
RMW-180/60-1200/ADH-O	F37103-000

Material Description	Material Number
RMW-180/60-1200/U-O	D87452-000
RMW-25/8-1200/ADH-O	782628-000
RMW-25/8-1200/U-O	A35258-000
RMW-25/8-490/U-O	CN2228-000
RMW-25/8-80/ADH-O	909858-000
RMW-35/12-1200/ADH-O	420356-000
RMW-35/12-1200/U-O	E76068-000
RMW-35/12-80/ADH-O	E93139-000
RMW-50/16-100/ADH-O	644770-000
RMW-50/16-1200/ADH-O	420494-000
RMW-50/16-1200/U-O	C36400-000
RMW-63/19-100/ADH-O	358414-000
RMW-63/19-1200/ADH-O	166916-000
RMW-63/19-1200/U-O	F61441-000
RMW-75/22-1200/ADH-O	934922-000
RMW-75/22-1200/U-O	F55912-000
RMW-85/25-1200/ADH-O	E52178-000
RMW-85/25-1200/U-O	D57524-000
RMW-95/29-1200/ADH-O	O68792-000
RMW-95/29-1200/U-O	D12371-000

**SAMPLE INVENTORY**

RMW-16/5-1200/ADH-O
RMW-25/8-1200/ADH-O
RMW-35/12-1200/ADH-O
RMW-50/16-1200/ADH-O
RMW-63/19-1200/ADH-O
RMW-75/22-1200/ADH-O
RMW-95/29-1200/ADH-O
RMW-160/50-1200/ADH-O
RMW-180/60-1200/ADH-O



[te.com/products/RMW](http://te.com/products/RMW)

**PROPERTY REQUIREMENTS**

Property	Unit	Requirement	Test Method
Dimensions	Inch (mm)	Table 1	ASTM D2671
Tensile Strength	psi (MPa)	1750 minimum (12)	ASTM D2671
Ultimate Elongation	Percent	350 minimum	ASTM D2671
Longitudinal Change	Percent	+5 to -15 maximum	ASTM D2671
Specific Gravity		1.2 maximum	ASTM D792
Hardness	Shore D	40 - 60	ASTM D2240
Low Temperature Flexibility 4 hrs @ -40°C		No cracking	ASTM D2671
Heat Resistance 168 h @150°C followed by Ultimate Elongation	Percent	350 minimum	ASTM D2671
Fungus Growth		Rating of 1 or less	ASTM G21
<b>ELECTRICAL</b>			
Dielectric Strength	V/mil (kV/cm)	300 minimum (120)	ASTM D149
Volume Resistivity	Ohm-cm	1 X 10 <sup>12</sup> minimum	ASTM D257
<b>CHEMICAL</b>			
Fluid Resistance 168 hrs @ 23°C Immersion in VDE 0370 oil followed by tests for:			
Tensile Strength	psi	1450 minimum (10)	ASTM D2671
Ultimate Elongation	Percent	300 minimum	
Corrosive Effect 16 hrs @ 150°C		Noncorrosive	ASTM D2671, Proc. A
Water Absorption 24 hrs @ 23°C	Percent	0.50 maximum	ASTM D570

**RMW & RHW ORDERING DESCRIPTION**


**Example 1:**

**RHW-130/36-1200/ADH-0**



**Example 2:**

**RMW-160/50-1200/U-0**



While TE has made every reasonable effort to ensure the accuracy of the information in this flyer, TE does not guarantee that it is error-free, nor does TE make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. TE reserves the right to make any adjustments to the information contained herein at any time without notice. TE expressly disclaims all implied warranties regarding the information contained herein, including, but not limited to, any implied warranties of merchantability or fitness for a particular purpose. The dimensions in this flyer are for reference purposes only and are subject to change without notice. Specifications are subject to change without notice. Consult TE for the latest dimensions and design specifications.

[te.com/products/RMW](http://te.com/products/RMW)

