# mail

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



# Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832 Email & Skype: info@chipsmall.com Web: www.chipsmall.com Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China





# SOFTFLEX GAP FILLER

## LIGHT FLEXIBLE THERMAL GAP FILLING PADS

The Aavid SoftFlex series is our most flexible and diverse line of thermal conductive pads. The compressibility and adhesion features enable a dramatic reduction in thermal resistance when mounting. The unique flexibility of the SoftFlex base material provides exceptional contouring and excellent cushioning performance. These defining features ensure that SoftFlex Gap Fillers are ideal for dealing with uneven surfaces, parts with varying heights and devices that require greater flexibility in design, all the while reducing overall stress to the PCB and eliminating tolerances.

#### **SIZES**

SoftFlex Thermal Interface Pads are available in full 400mm x 200mm sheets that Aavid can cut and shape to suit your needs. They are also available in easy to use 25.4mm x 25.4mm (1''x 1'') and 76.2mm x 76.2mm (3''x 3'') pads for quick and simple assembly.

### **PART NUMBERS**

Part Numbers for Aavid Gap Pads are made up of six sections that represent the product, thickness, adhesion and size. Instructions on how to build your part numbers are available in the document *Building an Aavid Gap Pad Part Number*.

## SOFTFLEX PRODUCT LINE DETAILS<sup>1</sup>



#### FEATURES:

- High Thermal Conductivity
- Reduced Thermal Resistance
- Wide Range of Hardness
- Flexible, Easy Contouring
- Single & Double Sided Adhesion
- Decreased Strain
- Puncture, Shear and Tear Resistant

Product Name	SoftFlex A014	SoftFlex B016	SoftFlex C022	SoftFlex D021	SoftFlex E038
Thermal Properties					
Thermal Conductivity (W/mK)	1.4	1.6	2.2	2.1	3.8
Operating Temp. Range (°C)	-40° - 150°	-40° - 150°	-40° - 150°	-40° - 150°	-40° - 150°
Thermal Resistance at 10psi (at % Strain) <sup>2</sup>	6.8 (at 24%)	4.6 (at 39%)	4.0 (at 28%)	5.0 (at 19%)	2.4 (at 18%)
Thermal Resistance at 20psi (at % Strain) <sup>2</sup>	6.0 (at 26%)	3.7 (at 43%)	3.4 (at 33%)	3.9 (at 21%)	2.0 (at 20%)
Thermal Resistance at 40psi (at % Strain) <sup>2</sup>	5.2 (at 30%)	3.6 (at 52%)	2.9 (at 42%)	2.3 (at 25%)	1.9 (at 24%)
Mechanical Properties					
Color	Blue/ Grey	Dark Grey/ Black	Pink/ Grey	Pink/ Light Pink	Grey/ Dark Grey
Adhesion	Single-Sided	Single-Sided	Single-Sided	Single-Sided	Double-Sided
Base Material	Silicone	Silicone	Silicone	Silicone	Silicone
Carrier / Reinforcement	PET Film				
Hardness (ASTM D2240, Shore 00)	36	37	34	48	71
Density (g/cm³)	1.8	2.0	2.9	2.9	3.1
Tensile Strength (kPa)	15	15	22	13	-
Thickness Availability (mm)	1, 2 or 3mm				
Electrical Properties					
Volume Resistivity (Ω-m)	≥10 <sup>10</sup>				
Breakdown Voltage (kVAC)	≥10	≥10	≥10	≥10	≥10
Flammability Rating UL94	V-0	V-0	V-1	V-1	V-0

<sup>1</sup> Measurement is for 1mm thickness, information on additional thicknesses is available on request.

<sup>2</sup>Strain is the ratio of the reduction in pad thickness to the initial thickness of the pad. Thermal resistance is measured in (°C x cm<sup>2</sup>/W).

USA: 1.855.322.2843 EUROPE: 39.051.764002 ASIA: 86.21.6115.2000 x8122



SoftFlex Gap Filler www.aavid.com July 2015 A01



DATASHEET