

Chipsmall Limited consists of a professional team with an average of over 10 year of expertise in the distribution of electronic components. Based in Hongkong, we have already established firm and mutual-benefit business relationships with customers from, Europe, America and south Asia, supplying obsolete and hard-to-find components to meet their specific needs.

With the principle of "Quality Parts, Customers Priority, Honest Operation, and Considerate Service", our business mainly focus on the distribution of electronic components. Line cards we deal with include Microchip, ALPS, ROHM, Xilinx, Pulse, ON, Everlight and Freescale. Main products comprise IC, Modules, Potentiometer, IC Socket, Relay, Connector. Our parts cover such applications as commercial, industrial, and automotives areas.

We are looking forward to setting up business relationship with you and hope to provide you with the best service and solution. Let us make a better world for our industry!



Contact us

Tel: +86-755-8981 8866 Fax: +86-755-8427 6832

Email & Skype: info@chipsmall.com Web: www.chipsmall.com

Address: A1208, Overseas Decoration Building, #122 Zhenhua RD., Futian, Shenzhen, China










Core **Toroid 63/38/25**



Effective parameters						
	Parameter	Value	Unit			
Σ(I/A)	core factor (C1)	0.497	mm ⁻¹			
Ve	effective volume	46500	mm³			
Le	effective length	ective length 152 mm				
Ae	effective area 306		mm²			
m	mass of core	≈ 220	g/pcs			

Epoxy coating DC isolation voltage 2000.

Maximum operating temperature of the coating is 200°C.

Dimensions (mm)						
Cores	OD	ID	н			
T63/38/25	63 ± 2	38 ± 1.2	25 ± 0.8	Uncoated		
TX63/38/25	65.5 max	36.4 min	26.3 max	Epoxy Coated		

Core data							
Cores	Material	Al (nH/turns²)	Al tolerance	μe			
T63/38/25	3C11	11000	± 25%	≈ 4300			
T63/38/25	3C94	5900	± 25%	≈ 2300			
T63/38/25	3E10	24400	± 20%	≈ 9500			
T63/38/25	3E26 (3E27-M7)	17900	± 25%	≈ 7000			
T63/38/25	3E27	14100	± 25%	≈ 5500			
T63/38/25	3E6 (3E10-M)	24400	± 30%	≈ 9500			
		Core data					
Cores	Material	Al (nH/turns²)	Al tolerance	μe			
TX63/38/25	3C11	11000	± 25%	≈ 4300			
TX63/38/25	3C94	5900	± 25%	≈ 2300			
TX63/38/25	3E10	24400	± 20%	≈ 9500			
TX63/38/25	3E26 (3E27-M7)	17900	± 25%	≈ 7000			
TX63/38/25	3E27	14100	± 25%	≈ 5500			
TX63/38/25	3E6 (3E10-M)	24400	± 30%	≈ 9500			